

# CONCRETE PIPE AND PORTAL CULVERT HANDBOOK

*P.I.P.E.S*



***Pipes, Infrastructural Products and  
Engineering Solutions Division***



## **PREFACE**

*Concrete pipes and portal culverts are the most frequently used and accepted products for stormwater drainage, culverts, outfall sewers and many other applications. To meet these needs South Africa's concrete pipe industry has grown tremendously over the past eighty years.*

*Modern technology and the acceptance of SABS standards ensure that products with consistently high quality are produced. Provided sound design and installation methods are followed, these products will give the desired hydraulic and structural performance over a long service life.*

*This handbook is intended to cover all aspects of concrete pipe and portal culvert selection, specification, and testing. As a handbook it does not attempt to replace textbooks or codes, but rather to complement them by providing the information needed for quick site decisions and guidance for designers to ensure that all aspects of product use are considered. A companion publication 'The Concrete Pipe and Portal Culvert Installation Manual' deals with product installation.*

*Publications by the American Concrete Pipe Association have been used freely and acknowledgement is hereby made to this organisation.*


*The Pipes, Infrastructural Products and Engineering Solutions (PIPES) Division of the Concrete Manufacturers Association has had this handbook prepared for the guidance of specifying bodies, consultants and contracting organisations using concrete pipes and portal culverts manufactured in accordance with the relevant SABS standards. The Division expresses appreciation to A.R. Dutton & Partners for the preparation of the original Concrete Pipe Handbook to which additions and amendments have been made to produce this publication.*

*Published by  
Concrete Manufacturers Association  
Block D, Lone Creek, Waterfall Office Park,  
Bekker Road, Midrand  
Telephone: +27 11 805 6742  
Fax: +27 86 524 9216  
Email: main.cma@gmail.com  
Website: www.cma.org.za  
Fifth Edition 2009*

<i>Revised by A. Goyns PIPES cc P O Box 12519 Clubview 0014</i>
---

# CONTENTS

<b>1. INTRODUCTION</b>		
1.1. OBJECTIVE	2	
1.2. SCOPE	2	
<b>2. PRODUCT CLASSIFICATION</b>		
2.1. STANDARDS	2	
2.2. CONCRETE PIPES	2	
2.3. PORTAL CULVERTS	4	
2.4. MANHOLES	6	
<b>3. HYDRAULICS</b>		
3.1. CONDUIT CLASSIFICATION	6	
3.2. HYDRAULIC LENGTH	7	
3.3. PRESSURE PIPELINES	7	
3.4. SEWERS AND STORMWATER OUTFALLS	8	
3.5. HYDRAULICS OF STORMWATER CULVERTS	9	
3.6. POROUS PIPES	15	
<b>4. LOADS ON BURIED PIPELINES</b>		
4.1. INTRODUCTION	16	
4.2. EARTH LOADS	17	
4.3. TRAFFIC LOADING	21	
<b>5. CONCRETE PIPE STRENGTHS</b>		
5.1. EXTERNAL LOADS	23	
5.2. INTERNAL PRESSURE	24	
5.3. SAFETY FACTORS	25	
5.4. SELECTION OF THE CONCRETE PIPE CLASS	25	
<b>6. BEDDING</b>		
6.1. GENERAL	26	
6.2. TRENCH AND NEGATIVE PROJECTION INSTALLATIONS	27	
6.3. POSITIVE PROJECTION INSTALLATIONS	30	
6.4. SOILCRETE BEDDING	31	
6.5. JACKING CONDITIONS	32	
<b>7. PIPE JOINTING</b>		
7.1. JOINT TYPES	32	
7.2. BUTT AND INTERLOCKING JOINT PIPES	33	
7.3. SPIGOT AND SOCKET JOINTS	33	
7.4. IN-THE-WALL JOINTS	33	
<b>8. FLOATATION</b>		
8.1. GENERAL	34	
8.2. FLOATATION BEFORE BACKFILLING	34	
8.3. FLOATATION AFTER BACKFILLING	34	
<b>9. SEWER CORROSION</b>		
9.1. CORROSION MECHANISM	35	
9.2. CORROSION PREDICTION AND CONTROL	35	
9.3. DEVELOPMENTS IN SOUTH AFRICA	36	
9.4. DESIGN AND DETAIL CONSIDERATIONS	38	
9.5. PIPE MATERIAL CHOICE FOR SEWERS	39	
9.6. SACRIFICIAL THICKNESS AND ALLOWABLE CRACK WIDTHS	41	
<b>10. PORTAL CULVERT STRENGTHS</b>		
10.1. GENERAL	41	
10.2. DETERMINING PORTAL CULVERT STRENGTHS	42	
10.3. PORTAL BASE SLABS	44	
<b>11. FIELD TESTING</b>		
11.1. WATER TEST	44	
11.2. AIR TESTING	45	
11.3. SOIL DENSITY TEST	45	
<b>BIBLIOGRAPHY</b>		<b>47</b>



## 1. INTRODUCTION

### 1.1. OBJECTIVE

The purpose of this handbook is to give the users, designers, specifiers and installers of precast concrete pipe and portal culverts the basic guidelines for the correct use, selection and specification of these products. A companion publication "The Concrete Pipe and Portal Culvert Installation Manual" gives details of how these products should be installed.

### 1.2. SCOPE

The content of this handbook covers the pre-construction activities associated with precast concrete pipe and portal culverts, namely those undertaken by the designer of the project. Descriptions are given of the basic theory needed for determining:

- product size
- product strength
- product durability
- special product features

The basic formulae, diagrams and tables support this. This information is adequate for most product applications. However, the theory given is by no means rigorous. The reader is advised to consult the relevant textbooks or codes, should a detailed analysis be required. A list of useful publications is given at the end of this handbook.

## 2. PRODUCT CLASSIFICATION

### 2.1. STANDARDS

There are three groups of standards which are applicable to precast concrete pipe and portal culverts, namely:

- Codes of practice that detail how product size, strength and durability should be selected.
- Product standards that prescribe what product requirements have to be met.
- Construction standards that prescribe how products should be installed.

The South African Bureau of Standards (SABS) has been restructured. The division dealing with the production of standards is Standards South Africa (StanSA). All the previously designated SABS standards are to be renamed

as South African National Standards (SANS) and will retain their numbers. This document uses the latter.

The division dealing with the issuing of manufacturing permits and the auditing of production facilities is Global Conformity Services (GCS). The products covered by this publication comply with the requirements of relevant (SANS) document. These are performance specifications that detail the properties of the finished products needed to ensure that they are suitable for their required application. All these standards have the same basic layout, namely:

- Scope
- Normative references
- Definitions
- Materials used
- Requirements to be met
- Sampling and compliance
- Inspection and test methods
- Marking
- Normative and informative annexures.

Most factories operated by the PIPES Division member companies have approved quality management systems to ensure that products comply with the relevant SANS specifications. In addition to this GCS, does frequent audits to check that standards are being maintained. These standards are periodically reviewed to ensure that marketplace requirements are met.

### 2.2. CONCRETE PIPES

#### 2.2.1. Standards

Currently there are two South African national standards applicable to concrete pipe:

- SANS 676 - Reinforced concrete pressure pipes
- SANS 677 - Concrete non-pressure pipes

The code of practice for the selection of pipe strength is:

- SANS 10102 - Part 1: Selection of pipes for buried pipelines: General provisions
- Part 2: Selection of pipes for buried pipelines: Rigid pipes

There are no standards for determining the size or durability of concrete pipe. If the reader requires more detail than given in this publication, reference should be made to the appropriate literature, some of which is detailed at the end of this publication.


The standards for the installation of concrete pipe are included as sections in SANS 1200 standardized specification for civil engineering construction. These sections are:

SANS 1200 DB - Earthworks (pipe trenches)  
 SANS 1200 L - Medium pressure pipe lines  
 SANS 1200 LB - Bedding (pipes)  
 SANS 1200 LD - Sewers  
 SANS 1200 LE - Storm water drainage  
 SANS 1200 LG - Pipe jacking

### 2.2.2. Pipe classes

#### Non-pressure pipe

Pipes are classified in terms of their crushing strength when subjected to a vertical knife-edge test-load. The two alternative crushing load test configurations are shown in Figure 1 (a) & (b).



**The proof load** is defined as the line load that a pipe can sustain without the development of cracks of width exceeding 0.25 mm or more over a distance exceeding 300 mm, in a two or three edge bearing test. Non-reinforced pipes are not permitted to crack under their proof load.

**The ultimate load** is defined as the maximum line load that the pipe will support in a two or three edge-bearing test and shall be at least 1.25 times the proof load.

The standard crushing load strength designation is the D-load (diameter load). This is the proof load in kilonewtons per metre of pipe length, per metre of nominal pipe diameter. The standard D-load classes with their proof and ultimate loads are given in Table 1.

**TABLE 1: STANDARD D-LOAD CLASSIFICATION FOR CONCRETE PIPES**

Pipe Class D-Load	Proof load kN/m	Ultimate load kN/m
25D	25xD	31.25xD
50D	50xD	62.50xD
75D	75xD	93.75xD
100D	100xD	125.00xD

#### Example:

For a 1050 mm diameter 75D pipe proof load =  $1.05 \times 75 = 78.75$  kN/m ultimate load =  $1.05 \times 93.75 = 98.44$  kN/m

Pipes made in accordance to SANS 677 are divided into two types,


- SC pipes for stormwater and culvert applications
- SI pipes for sewer and irrigation applications.

SC pipes are used in applications where there is no internal pressure. A small sample ( $\pm 2\%$ ) of pipes is subjected to the crushing strength test to prove that they meet the strength required. SI Pipes, on the other hand, are used in applications where there could be internal pressure under certain conditions (as when blockages occur). To ensure that the pipes will meet this possible condition and ensure that the joints are watertight, a small sample of pipes is hydrostatically tested to a pressure of 140 kilopascals in addition to the crushing strength test.

Table 2 gives proof loads of the preferred nominal diameters given in SANS 676 and 677.

**TABLE 2: PREFERRED CONCRETE PIPE DIAMETERS AND PROOF LOADS IN- KN/M**

Nominal Pipe Diameter-mm	D Loads in Kilonewtons/m			
	25D	50D	75D	100D
300	-	15.0	22.5	30.0
375	-	18.8	28.1	37.5
450	-	22.5	33.8	45.0
525	13.1	26.3	39.4	52.5
600	15.0	30.0	45.0	60.0
675	16.9	33.8	50.6	67.5
750	18.3	37.5	56.3	75.0
825	20.6	41.3	62.0	82.5
900	22.5	45.0	67.5	90.0
1 050	26.3	52.5	78.8	105.0
1 200	30.0	60.0	90.0	120.0
1 350	33.8	67.5	101.3	135.0
1 500	37.5	75.0	112.5	150.0
1 800	45.0	90.0	135.0	180.0



## Notes

- 1) Pipes with diameters smaller than 300 mm, or larger than 1 800 mm are made at some factories.
- 2) Strengths greater than 1000 can be produced to order.
- 3) Most pipes are made in moulds with fixed outside diameters. The designer should check minimum the internal diameters to ensure that requirements are met.

## Pressure pipe

Pressure pipes are classified in terms of their hydraulic strength when subject to an internal pressure test under factory conditions.

**Hydraulic strength** is defined as the internal pressure in bar that the pipe can withstand for at least 2 minutes without showing any sign of leakage. The standard hydraulic strength designation is the test (T) pressure. The SANS 676 pressure classes are given in Table 3.

**TABLE 3: STANDARD PRESSURE CLASSES FOR PIPE**

Pipe class	Test pressure	
	Bars	Kilopascals
T2	2	200
T4	4	400
T6	6	600
T8	8	800
T10	10	1 000

## Special-purpose pipe

Many pressure pipelines are installed at a nominal fill and where they are not subject to traffic loads. Under these circumstances the hydraulic strength designation, given in Table 3, is adequate.

However, when a pipeline is subject to the simultaneous application of internal pressure and external load, the pipes will need to sustain a higher hydraulic pressure and crushing strength than when service loads are applied separately.

Under these conditions the pipes will be classified as special-purpose pipes and the required hydraulic test pressure and crushing strength to meet the required installed conditions will have to be calculated. These pipes must be specified in terms of both their D-load and T-pressure values.

## 2.3. PORTAL CULVERTS

### 2.3.1. Standards

The standard for precast concrete culverts is SANS 986, precast reinforced concrete culverts.

There is no National code of practice for the selection of portal culvert size or strength. However, the biggest single group of users, the national and provincial road authorities, require that portal culverts under their roads meet the structural requirements of TMH7, the Code of Practice for the Design of Highway Bridges and Culverts in South Africa. The local authorities generally adhere to the requirements of this code. This document also gives guidelines for product durability.

If more detail than provided in this document is required, reference should be made to the appropriate literature, some of which is listed at the end of this publication.

The standards for the installation of precast portal culverts are included in sections 1200DB and 1200LE of the SANS 1200 series.

### 2.3.2. Portal Culvert Classes

Precast portal culverts are classified in terms of their crushing strength, when subjected to a combination of loading cases involving vertical and horizontal knife-edge test-loads under factory conditions. The proof and ultimate loads are defined in the same way as for pipes with the ultimate loads being 1.25 times the proof loads for the particular loading configurations.

The standard crushing strength designation used is the S-load. (Span-crushing load) This is the vertical component of the proof load in kilonewtons that a 1 metre length of culvert will withstand, divided by the nominal span of the portal culvert in metres.

There are three different loading configurations that are applied to precast portal culverts to model the installed conditions, namely:

- Deck bending moment and sway
- Deck shear
- Inner leg bending moment and shear

These configurations are shown respectively in Figure 2(a), (b) and (c) below and the standard S-load classes with their proof load requirements are given in Table 4.

Figure 2: Load test configurations for precast portal culverts




TABLE 4: STANDARD S-LOAD CLASSIFICATION FOR PORTAL CULVERTS


Culvert class S-Load	Proof loads - kN/m of length		Leg Proof loads - kN/m of length	
	Vertical	Horizontal	Height > S/2	Height = S
75S	75 x S	30	0.4 x 75 x S	0.60 x 75 x S
100S	100 x S	30	0.3 x 100 x S	0.50 x 100 x S
125S	125 x S	30	0.2 x 125 x S	0.45 x 125 x S
150S	150 x S	30	0.2 x 150 x S	0.43 x 150 x S
175S	175 x S	30	0.2 x 175 x S	0.40 x 175 x S
200S	200 x S	30	0.2 x 200 x S	0.40 x 200 x S

Note: S is the nominal span in metres.

Table 5 gives the vertical and horizontal proof loads obtained by applying the classification in Table 4 to the preferred portal culvert dimensions given in SANS 986. A table similar to Table 5 can be obtained by application of the values in Table 4 to obtain the inner leg bending moments and shears. It should be noted that there will be two different values of the horizontal load for each culvert span and class, i.e. when  $0.5 < H/S < 1.0$  and  $H/S = 1.0$ . When  $H/S < 0.5$  no horizontal leg load is required.

TABLE 5: PREFERRED PORTAL CULVERT DIMENSIONS AND PROOF LOADS

Culvert span mm	Vertical proof loads in kN/m of length					Horizontal proof load all classes kN/m Culvert Class
	Culvert Class					
	75S	100S	150S	175S	200S	
450	-	-	-	-	90.0	30
600	-	-	-	-	120.0	
750	-	-	-	131.3	-	
900	-	-	-	157.5	-	
1200	-	-	180.0	-	-	
1500	-	150.0	-	-	-	
1800	135.0	-	-	-	-	
2100	157.5	-	-	-	-	
2400	180.0	-	-	-	-	
3000	225.0	-	-	-	-	
3600	270.0	-	-	-	-	



## 2.4. MANHOLES

### 2.4.1. Standards

The standard for precast concrete manhole sections, slabs, lids and frames is SANS 1294.

The standard manhole dimensions are hard metric, namely:

- 750 mm diameter - used as shaft sections
- 1 000 mm diameter - normally used as chamber sections
- 1 250 mm diameter - used as chamber sections
- 1 500 mm diameter - used as chamber sections
- 1 750 mm diameter - used as chamber sections

These sections are available in lengths of 250 mm, 500 mm, 750 mm and 1 000 mm.

In the past manholes were produced in soft metric dimensions. Hence when components have to be replaced it is essential that actual details and dimensions be checked before ordering replacements as old sizes are no longer available and it may be necessary to replace the whole manhole.

Currently SANS 1294 is being revised. When this standard is released, a detailed section on manholes will be added to this publication.

## 3. HYDRAULICS


### 3.1. CONDUIT CLASSIFICATION

Conduits conveying fluids are classified by various parameters, namely, whether:

- They flow as open channels or closed conduits
- The flow is uniform, in which case the flow depth, velocity and discharge along the whole length of the conduits are constant. If not uniform, the flow is varied
- The flow is steady in which case the flow past a given point has a constant depth, velocity and discharge. If not steady, the flow is unsteady.

A pipeline conveying potable water or other fluids generally flows full and operates under pressure and the flow is both uniform and steady. The total energy in such a system will have three components, namely conduit height or diameter, velocity head and pressure head as shown in Figure 3.

Figure 3: Conduit flowing full



The total energy at any point along a conduit operating under pressure can be defined by Bernoulli's equation:

$$H = z + d/2 + h_p + v^2/2g$$

Where  
 $z$  - height of invert above datum in m  
 $d$  - conduit height or diameter in m  
 $v$  - velocity in m/s  
 $g$  - gravitational constant in m/s/s  
 $h_p$  - pressure head in pipeline in m  
 $h_f$  - energy loss due to friction in m


As there is pressure in such a conduit, the fluid can be carried uphill provided the value of " $h_p$ " stays positive. Such a system is classified as a pressure pipeline.

On the other hand, a conduit conveying stormwater or sewage generally flows partly full and the flow is frequently both varied and unsteady. There is an air/fluid interface and therefore, no pressure component to the total energy as shown in Figure 4.

Figures 3 and 4 show systems where the pipe invert, hydraulic grade line or water surface and the total energy line are all parallel. This is called uniform flow and the only energy losses are due to friction. However if there are any transitions such as changes in vertical or horizontal alignment, or the cross-sectional shape of the conduit then these will also cause energy losses due to the liquid expanding or contracting.

The means of determining the hydraulic properties of conduits flowing under pressure and those flowing partly full, as open channels are understandably different. A further factor that needs to be considered is the hydraulic length of the conduit.

Figure 4: Conduit flowing partly full



The total energy at any point along a conduit flowing partly full can be defined by the energy equation:

$$H = y + \frac{v^2}{2g}$$

Where  $y$  - depth of flow in m  
 $v$  - velocity in m/s  
 $g$  - gravitational constant in m/s/s

As there is no pressure in such a conduit, the fluid can only flow downhill and the system is classified as a gravity pipeline.

### 3.2. HYDRAULIC LENGTH

The hydraulic length of a conduit is determined by the relationship between the energy losses due to friction and those due to transitions. When the energy losses due to friction exceed those due to transitions then the conduit is classified as hydraulically long. When those due to transitions exceed those due to friction then the conduit is classified as hydraulically short. In general a pipeline is hydraulically long whereas a culvert crossing is hydraulically short.

The energy losses due to friction are determined using one of the friction formulae, such as Manning, to calculate the velocity through the conduit. Manning's equation is given below:

$$v = 1/n(R)^{2/3}S^{1/2}$$

where  $v$  - velocity in m/s  
 $n$  - Manning's roughness coefficient  
 $R$  - hydraulic radius  
 $S$  - gradient of conduit

The energy losses due to transitions in a conduit can be determined theoretically by comparing flow areas

before and after the transition. For most applications the use of a coefficient as shown in the formula below, is adequate:

$$H_L = k(v^2/2g)$$

where  $H_L$  - head loss in metres (m)  
 $k$  - a coefficient, usually between 0.0 and 1.0 dependent upon transition details  
 $v$  - velocity in metres per second (m/s)  
 $g$  - the gravitational constant in metres per second per second (m/s/s)

Commonly used energy loss coefficients are given in Table 6 below.

TABLE 6: ENERGY LOSS COEFFICIENTS FOR PIPELINE FLOW

Entrance or outlet detail	Entrance	Outlet
Protruding	0.80	1.00
Sharp	0.50	1.00
Bevelled	0.25	0.50
Rounded	0.05	0.20

The friction slope of a pipeline that has no transitions is the energy difference between inlet and outlet, divided by the pipeline length. If there are any transitions in the pipeline, the energy losses due to the transitions will reduce the amount of energy available to overcome friction.

### 3.3. PRESSURE PIPELINES

The hydraulic performance (velocity and discharge) of a pressure pipeline is determined by using one of the friction formulae such as Manning, in combination with the continuity equation and energy losses at transitions.



The continuity equation is

$$Q = Av$$

Where  $Q$  - discharge in cubic metres per second (m<sup>3</sup>/s)

$A$  - cross-sectional area in square metres (m<sup>2</sup>)  
 $v$  - velocity in metres per second (m/s)


Most low-pressure pipelines flow under gravity and have no additional energy inputs, i.e. no use is made of additional energy to lift the water. If pressure is added to the pipeline by a pump, the energy is increased.



An alternative approach to determining the hydraulic properties of a pipeline is to use a chart for a pipe flowing full as given in Figure 5 and to add any energy inputs or subtract any energy losses at transitions. If

the pipeline is flowing under pressure the friction slope should be used, as this will probably be different from the pipeline gradient that could vary along the length of the pipeline.

Figure 5: Flow chart for circular pipes based on Manning formula



### 3.4. SEWERS AND STORMWATER OUTFALLS

Most sewer and storm water outfalls consist of sections of hydraulically long conduit flowing partly full between transitions (manholes). If the pipeline is flowing partly full then the slope of the energy line and the pipeline gradient will be the same.

Under these circumstances the sections of pipeline between manholes can be evaluated by using the chart for pipes flowing full, Figure 5 and then adjusting the values using proportional flow as given in Figure 6 that gives the relationship between the relative depth  $d/D$  and the other parameters as hydraulic radius, velocity and discharge. Examples of the combined use of these figures are given below Figure 6.


Example 1: Given a 600 mm internal diameter ( $D$ ) concrete pipeline at a slope of 1 in 1 000 and a discharge of 120 litres per second ( $V_s$ ), determine velocity and flow depth. Use  $n = 0.011$ .

From the flow chart intersecting the co-ordinates of diameter (600) and slope (1 in 1 000) we obtain:

$$Q = 240 \text{ l/s and } V = 0,82 \text{ m/s}$$

Then  $Q/Q_{full} = 120/240 = 0.5$  and Figure 6 gives  $d/D = 0.5 \times 600 = 300 \text{ mm}$  and  $v/v_{full} = 1.0 \times 0.82 = 0.82 \text{ m/s}$

Figure 6: Relative flow properties of circular pipe flowing partly full



Example 2: Given a flow of 200 l/s and a slope of 1 m in 2 000 m, determine the diameter of a concrete pipe to flow half full.

Use  $n = 0,011$

From Figure 6 for  $y/D = 0.5$ ;  $Q_{full} = Q/0.5 = 200/0.5 = 400$  l/s and from Figure 5 for  $Q = 400$  l/s and a slope of 1 m in 2 000 m,  $D = 900$  mm.

### 3.5. HYDRAULICS OF STORMWATER CULVERTS

The capacity of hydraulically short conduits, such as stormwater culverts is predominantly dependent upon the inlet and outlet conditions. These conduits seldom


flow full and the energy losses at inlets and outlets due to sudden transitions far exceed any losses due to friction. Under these circumstances, the charts for pipes flowing full should not be used.


For stormwater culverts the most important hydraulic considerations are:

- Headwater level at the entrance that will determine upstream flooding.
- Roadway overtopping necessitating road closure.
- Outlet velocity that could cause downstream erosion.

The various factors that will influence the flow through a hydraulically short conduit, such as a culvert under a road are illustrated in Figure 7 below.

Figure 7: Factors influencing flow through culverts






Where  $HW$  - headwater or energy level at inlet in m  
 $TW$  - tailwater or energy level at outlet in m  
 $H$  - total energy loss between inlet and outlet in m  
 $D$  - internal diameter or height of conduit in m  
 $L$  - length of conduit in m  
 $S_o$  - culvert gradient in m/m

There are several different types of culvert flow, depending on whether the control is located at the inlet, along the barrel or at the outlet.

Inlet control occurs when the inlet size, shape and configuration controls the volume of water that can enter the culvert. In other words when the capacity of the inlet is less than the capacity of the barrel and there is a free discharge downstream of the culvert.

Figure 8: Inlet control condition and variations



This happens when the slope of the culvert is steeper than the critical slope. When the conduit flows with an unsubmerged inlet, the flow passes through critical depth at the entrance to the culvert. When the culvert flows with a submerged inlet, which will occur when  $HW/D > 1.5$ , the inlet will act as an orifice and the flow will contracted as if flowing through a sluice gate.


The major energy loss will be at the culvert inlet. The total energy through the culvert and the outlet velocity can be calculated from the critical or contracted depth at the entrance.

Barrel control occurs when the barrel size, roughness and shape controls the volume of water that which

can flow through the culvert. In other words when the capacity of the barrel is less than the capacity of the inlet and the discharge downstream of it is free.


This happens when the slope of the culvert is flatter than critical slope and the constriction at the entrance is drowned out by the flow through the barrel. The major energy loss will be at the outlet. The water surface will pass through critical depth at the outlet and the outlet energy level and velocity can be calculated from this, as described below.

Figure 9: Barrel control conditions and variations



Outlet control occurs when the water level downstream of the culvert controls the volume of water that can flow through the culvert by drowning out either inlet or barrel control conditions. In other words when the capacity of the barrel or the inlet cannot be realised because there is no free discharge downstream of the culvert.


Figure 10: Outlet control condition and variation



The water surface will not pass through critical depth at any section of the culvert hence there are no sections where there is a fixed depth discharge relationship. The major energy loss will be at the outlet.

The capacity and headwater depths for the different types of culvert flow can be determined by calculation or from nomographs.

Figure 11: Headwater depth: concrete pipe culverts: inlet control






Figure 12: Headwater depth: concrete pipe culverts: outlet control





Figure 13: Headwater depth: rectangular culverts: inlet control







Figure 14: Headwater depth: rectangular culverts: outlet control



### 3.5.1. Capacity and Headwater Depth for Hydraulically Short Conduits

When gradients are steep and the flow of water at the outlet of the pipe is partially full, the control will be at the inlet. In other words, more water can flow through the culvert than into it. The capacity and headwater levels for a circular concrete pipe culvert operating under inlet control can be determined using the nomograph given in Figure 11.

When gradients are very flat or the outlet of the culvert is submerged, the control will be either through the barrel or at the outlet. In other words, more water can flow through the entrance to the culvert than through the barrel. The capacity and headwater levels for a circular concrete pipe culvert operating with either barrel or outlet control can be determined using the nomograph given in Figure 12.

However, the outlet velocity for the flow through culverts needs to be calculated.

The capacity and headwater levels for a rectangular concrete culvert operating under inlet control can be determined using the nomograph given in Figure 13 and that for a rectangular concrete culvert operating with outlet control is given in Figure 14.

### 3.5.2. Outlet Velocity for Hydraulically Short Conduits

Outlet velocity is seldom calculated for culverts, yet it is this that causes downstream erosion and wash-aways that can result in recurring maintenance costs. The exact calculation of outlet velocities is difficult. However, conservative estimates can be made using the procedures that follow.

For culverts flowing with inlet or barrel control, the outlet velocity can be calculated by identifying the control point at the entrance or outlet where the depth discharge relationship is fixed. For a culvert of any cross-sectional slope, the critical depth will occur when

$$Q^2T / gA^3 = 1$$

Where:  $Q$  - discharge in  $m^3/s$   
 $T$  - flow width in  $m$   
 $G$  - gravitational constant in meters/second per second ( $m/s/s$ )  
 $A$  - flow area in  $m^2$

For a rectangular section this reduces to

$$dc = vc^2 / g$$

Where:  $dc$  - the critical depth in  $m$   
 $vc$  - the critical velocity in  $m/s$

There is no simple equation for the relationship between critical depth and velocity in a circular pipe. However, the use of the above equation will over estimate the velocity by about 10%. Hence, it will be adequate for most stormwater drainage applications.

For the inlet control condition with an unsubmerged inlet, the outlet velocity can be calculated from the critical energy level at the inlet to the culvert. If the inlet is submerged, the outlet velocity can be calculated from the energy level at the inlet, which is obtained by subtracting the inlet energy loss from the headwater depth. This is calculated using the relevant coefficient from Table 6.

For the barrel control condition, the flow will pass through critical depth at the outlet and the outlet velocity can be calculated from this.


For the outlet control condition, outlet velocity should not be a problem as it is the downstream conditions that drown the flow through the culvert. If the outlet is not submerged, the outlet velocity can be calculated by assuming that the flow depth is the average of the critical depth and the culvert height in diameter. If the outlet is submerged, the outlet velocity will be the discharge divided by culvert area.

## 3.6. POROUS PIPES

Porous pipes are used as a means of subsoil drainage and have the following applications:

- Subsurface drainage under roads and railways where the presence of seepage water from a high water table would be detrimental to the foundations of the road or railway
- Under reservoirs and other water retaining structures where the effects of leaks and uplift can be minimised and controlled by subsoil drainage
- Under large areas such as parks, airports and agricultural holdings, where the subsoil must be well drained.

Designing a subsoil drainage system is based on the same hydraulic principles as normally used for determining pipe sizes. The primary problem is determining the flow, which is dependent on soil characteristics, the area to be drained and rainfall. The flow in the subsoil drainage system will depend on the judgement of the designer. Table 7 below gives some guidelines.



**TABLE 7: APPROXIMATE FLOW LITRES/SEC PER HECTARE: VARIOUS CONDITIONS**

Soil Type	Rainfall per annum – mm			
	<750	750 - 1000	1000 - 1200	>1200
Clays	0.45	0.55	0.75	1.20
Loams	0.60	0.80	1.00	1.70
Sandy soils	0.85	1.10	1.50	2.40

The optimum spacing and depth of a subsoil drain is largely dependent on the type of soil. Where large areas are to be drained Table 8, that gives the capacity of porous pipes and Table 9, that gives a guide to spacing in metres for various soils and drain installation depths can be used to estimate the size and spacing of pipes for a subsoil drainage system.

**TABLE 8: FLOW CAPACITY OF POROUS PIPES IN LITRES/SEC**

Internal diameter (mm)	Slope of pipe in m/m				
	0.001	0.005	0.01	0.05	0.10
100	1.2	2.7	3.9	8.6	12.2
150	3.6	8.1	11.4	25.8	36.4
200	8.3	18.3	26.1	58.9	82.8
300	25.8	57.8	81.9	183.3	258.3

Although a slope of 0.001 is theoretically possible, slopes of less than 0.005 are not practical. The spacing of drains, not hydraulic considerations, normally controls the design of a system.

**TABLE 9: POROUS PIPE SPACING IN METRES FOR DIFFERENT SOIL TYPES**

Pipe depth in m	Clays	Loams	Sandy clay
0.6 - 0.9	7 - 10	10 - 12	12 - 25
0.9 - 1.2	9 - 12	12 - 15	25 - 30

Although the tables only indicate sizes up to 300 mm in diameter, larger sizes may be available from certain pipe manufacturers. As there is no South African standard for these pipes the porosity standards from BS 1194, as given in Table 10 are used. The manufacturers should be asked for details of the crushing strengths for porous pipes.

**TABLE 10: POROSITY VALUES IN LITRES/SEC PER METRE OF PIPE LENGTH**

Pipe diameter in mm	100	150	200	300
Porosity litre per sec per metre length	1.0	2.0	2.5	5.0

## 4. LOADS ON BURIED PIPELINES

### 4.1. INTRODUCTION

Every buried pipeline is subjected to loads that cause stresses in the pipe wall. These loads can be broadly defined as primary loads and secondary loads. Primary loads can be calculated and include:

- mass of earth fill above pipe
- traffic loading
- internal pressure loading.

Other primary loads are pipe and water masses that can be ignored, except in critical situations.

Secondary loads are not easy to calculation as they are variable, unpredictable and localised. They can however cause considerable damage to a pipeline due to differential movements between pipes. It is therefore essential that their potential impact be recognised and that where necessary that precautions are taken. Examples of factors that could cause secondary loads are:

- Volume changes in clay soils due to variations in moisture content
- Pressures due to growth of tree roots
- Foundation and bedding behaving unexpectedly
- Settlement of embankment foundation
- Elongation of pipeline under deep fills
- Effects of thermal and moisture changes on pipe materials and joints
- Effects of moisture changes and movements on bedding
- Restraints caused by bends, manholes etc.

It is preferable to avoid or eliminate the causes of these loads rather than attempt to resist them.

Where this is not possible, particular attention must be paid to pipe joints and the interfaces between the pipeline and other structures, such as manholes to ensure that there is sufficient flexibility. The reader is referred to the section of this handbook dealing with joints.

Where pipelines operate in exposed conditions such as on pipe bridges or above ground, the pipes will be subject to thermal stresses and longitudinal movement. The thermal stresses are caused by temperature differences between the inside and outside of the pipe that alternate between night and day resulting in the pipe walls cracking due to cyclical strains. This is generally not a problem when the pipe walls are less than 100mm thick. The longitudinal movement is caused by the expansion and contraction of the pipeline due to temperature changes.

The design of the pipe and pipeline for such conditions should be discussed with a competent manufacturer or specialist consultant so that the necessary precautions can be taken to cope with these effects and ensure that the pipeline will operate satisfactorily. These are beyond the scope of this handbook.

## 4.2. EARTH LOADS


The calculation of earth loads on a buried conduit from first principles is complex. For a thorough understanding, reference should be made to the specialist literature and SANS 10102 Parts 1 and 2. The prime factors in establishing earth loads on buried conduits are:

- installation method
- fill height over conduit
- backfill density
- trench width or external conduit width

To use the tables in this handbook, it is necessary to understand the various methods of installing buried conduits. The two basic installation types and the corresponding loading conditions are the trench and the embankment conditions. These are defined by whether the frictional forces developed between the column of earth on top of the conduit and those adjacent to it reduce or increase the load that the conduit has to carry.

A useful concept is that of the geostatic or prism load. This is the mass of earth directly above the conduit assuming that there is no friction between this column of material and the columns of earth either side of the conduit. The geostatic load will have a value between that of the trench and embankment condition. These loading conditions are illustrated in Figure 15 below.

Figure 15: Comparison of trench, geostatic and embankment loading



### 4.2.1. Trench condition


The trench condition occurs when the conduit is placed in a trench that has been excavated into the undisturbed soil. With a trench installation the frictional forces that develop between the column of earth in the trench and the trench walls act upwards and reduce the load that the conduit has to carry. As a result the load on the conduit will be less than the mass of the material in the trench above it. The load on the conduit is calculated from the formula:

$$W = C_t w B_t^2$$

Where

- $W$  - load of fill material in kN/m
- $w$  - unit load of fill material in kN/m<sup>3</sup>
- $B_t$  - trench width on top of conduit in m
- $C_t$  - coefficient that is function of fill material, trench width and fill height

The formula indicates the importance of the trench width  $B_t$  that should always be kept to a practical minimum. As the trench width is increased so is the load on the conduit. At a certain stage the trench walls are so far away from the conduit that they no longer help it carry the load. The load on the conduit will then be the same as the embankment load. If the trench width exceeds this value the load will not increase any more. This limiting value of  $B_t$  at which no further load is transmitted to the conduit, is called the transition width.



The determination of the transition width is covered in the specialist literature. It is safe to assume that any trench width that gives loads in excess of those given by the embankment condition exceeds the transition width.

Earth loads due to trench loading on circular pipe where the trench widths and nominal pipe diameters are specified are given in Table 11. Earth loads due to trench loading on conduits where the trench widths are specified but the conduit dimensions are not are given in Table 12.

**TABLE 11: TRENCH LOADS ON CIRCULAR PIPE IN KN/M; NON-COHESIVE SOIL (GROUP NO 1 SANS 10102 PART 1); TRENCH WIDTHS SANS 1200 DB**

Diameter mm	Trench width m	Height of backfill above top of pipe in metres										
		0.6	1.0	1.5	2.0	2.5	3.0	3.5	4.0	5.0	6.0	7.0
225	0.859	9	15	21	26	30	34	37	40	44	48	50
300	0.945	10	17	23	29	34	39	42	46	51	56	59
375	1.031	11	18	26	32	38	43	48	52	59	64	68
450	1.118	13	20	28	36	42	48	54	58	66	72	77
525	1.204	14	22	31	39	47	53	59	64	74	81	87
600	1.290	15	23	33	42	51	58	65	71	81	90	97
675	1.376	16	25	36	46	55	63	70	77	89	99	107
750	1.663	19	31	44	57	69	80	90	99	115	129	141
825	1.749	20	32	47	61	73	85	95	105	123	139	152
900	1.835	21	34	50	64	77	90	101	112	131	148	163
1050	2.208	26	42	61	79	96	112	127	141	167	190	210
1200	2.380	28	45	66	86	104	122	138	154	183	209	233
1350	2.620	31	50	73	95	116	136	155	173	207	237	264
1500	2.800	33	53	78	102	125	147	167	187	224	258	288
1650	2.980	35	57	84	109	134	157	180	201	242	278	312
1800	3.360	39	65	95	125	153	180	206	231	279	323	363

**Notes**

1. For nominal pipe diameters  $\leq 1200\text{mm}$  the external diameter has been taken as 1.15 times the nominal diameter; for larger sizes 1.2 times the nominal diameter.
2. Table 11 for non-cohesive soil; gravel or sand; density =  $20 \text{ kN/m}^3$  and  $K_u = 0, 19$ .
3. The table is based on the trench widths recommended in SANS 1200DB.

4. If the soil unit weight is known, the loads from the table may be adjusted as follows: Load on pipe = load from table  $\times$  unit weight of soil / 20
5. This procedure is valid only if the soil properties other than unit weight do not change.

Note that Table 12 is for the same installation conditions and soil properties used in Table 11.

**TABLE 12: LOADS ON ANY CONDUIT IN KN/M FOR GIVEN TRENCH WIDTHS**

Trench Width in m	Height of Backfill above top of pipe in metres										
	0.6	1.0	1.5	2.0	2.5	3.0	3.5	4.0	5.0	6.0	7.0
0.75	8	13	18	22	25	28	30	32	36	38	39
1.00	11	18	25	31	37	42	46	50	56	61	64
1.25	14	23	32	41	49	56	62	68	78	86	92
1.50	17	28	40	51	61	70	79	87	100	112	122
2.00	23	38	55	70	85	99	112	125	147	167	184
2.50	29	47	69	90	110	129	147	164	195	223	249
3.00	35	57	84	110	135	159	181	203	243	281	315
3.50	41	67	99	130	160	188	216	242	292	339	382
4.00	47	77	114	150	185	218	250	282	342	397	450
5.00	59	97	144	190	234	278	320	361	440	515	587

#### 4.2.2. Embankment condition

In this condition the conduit is installed at ground level and is covered with fill material. All the earth surrounding the conduit is homogeneous and the compaction is uniform. With an embankment installation the frictional forces that develop between the column of earth directly above the conduit and the columns of earth adjacent to the conduit, act downwards and increase the load that the conduit has to carry. The load on the conduit will be greater than the mass of the material directly above it due to the frictional forces that develop. In addition the founding material under the conduit could yield and partly reduce the load that it has to carry. The load on a conduit is calculated from the formula:

$$W = w C_e B_c^2$$

Where  $W$  - load on pipe in kN/m  
 $w$  - unit load on fill material in kN/m<sup>3</sup>  
 $B_c$  - overall diameter of pipe  
 $C_e$  - coefficient that is function of fill material, conduit outside width, fill height, projection ratio, and founding conditions

The projection ratio is a measure of the proportion of the conduit over which lateral earth pressure is effective. It is calculated from  $p = x / B_c$ , where  $x$ =height that conduit projects above or below the natural ground level

The settlement ratio, designated as  $r_s$ , is a measure of the amount that the founding material under the conduit settles.

Values of this parameter are given in Table 13 below.

Earth loads due to embankment loading on circular pipes are given in Table 14.

**TABLE 14: POSITIVE PROJECTION EMBANKMENT LOADING IN KN/M ON A BURIED CONDUIT; NON-COHESIVE MATERIAL; DENSITY 20 KN/M<sup>3</sup>,  $K\mu = 0.19$ ;  $Pr_s = 1.0$**

Diameter mm	Height of backfill above top of pipe in metres										
	0.6	1.0	1.5	2.0	2.5	3.0	3.5	4.0	5.0	6.0	7.0
225	5	9	13	17	22	26	31	35	44	52	61
300	6	12	17	23	29	35	41	47	58	70	82
375	7	14	22	29	36	44	51	58	73	87	102
450	8	15	26	35	44	52	61	70	87	105	122
525	9	17	30	41	51	61	71	82	102	122	143
600	10	18	32	47	58	70	82	93	117	140	163
675	11	20	35	52	66	79	92	105	131	157	184
750	12	22	37	56	73	87	102	117	146	175	204
825	13	23	39	59	80	96	112	128	160	192	224
900	14	25	42	61	85	105	122	140	175	210	245
1050	16	28	46	68	92	121	143	163	204	245	286
1200	18	32	51	74	100	129	163	187	233	280	327
1350	21	37	58	83	111	142	177	216	274	329	383
1500	23	40	64	90	119	151	187	228	304	365	426
1650	25	44	69	97	127	161	199	240	335	402	468
1800	27	47	74	104	136	171	210	252	348	438	511


Notes:

- 1) Table 14 compiled for non-cohesive material with density of 20 kN/m<sup>3</sup> and  $Pr_s = 1.0$
- 2) Table 14 can be used for other soil densities by multiplying load by actual density /20
- 3) Table 14 can be used for different values of  $Pr_s$  as follows:
  - (a) If load is to the left of shaded area, it may be used irrespective of the  $Pr_s$  value.
  - (b) If load falls in the shaded area, multiply the value by the following factors:

$Pr_s$	1.0	0.7	0.5	0.3	0.1
Factor	1.00	0.94	0.90	0.83	0.74

**TABLE 13: VALUES OF SETTLEMENT RATIO**

Material type	Rock	Unyielding soil	Normal soil	Yielding soil
Settlement ratio, $r_s$	1.0	1.0	0.7	0.3




The various types of embankment condition, illustrated in Figure 16 are:

- Positive projection where top of the conduit projects above the natural ground level.
- Zero projection where the top of conduit is level with natural ground. The load on the pipe is the geostatic load. This also applies if the side fill

to a sub-trench is compacted to the same density as the undisturbed soil in which the trench has been dug.

- Negative projection where top of the conduit is below the natural ground level. As the trench depth increases, this condition approaches a complete trench condition.

Figure 16: Types of embankment installation.



**Example 1.** Determination of backfill load under the following conditions: Embankment installation, positive projection. Pipe  $D = 525$  mm; Projection ratio:  $x/D = 0.7$ ; Foundation material: rock ( $r_s = 1$ ); Density of fill:  $1750 \text{ kg/m}^3$ ; Height of fill above top of pipe:  $3.5 \text{ m}$ .

$Pr_s = 0.7 * 1 = 0.7$ ; Table 14 applicable with correction for density only. For  $D = 525$  mm and height =  $3.5 \text{ m}$ , Load on pipe =  $68.0 \text{ kN/m}$ . Applying density correction, the actual load on pipe,  $W = 68(1750/2000) = 59.5 \text{ kN/m}$ .

**Example 2.** Determination of backfill load under the following conditions: Embankment installation, positive projection; Pipe  $D = 750$  mm; Projection ratio =  $0.70$ ; Foundation material: ordinary soil: ( $r_s = 0.7$ ); Density of fill:  $1600 \text{ kg/m}^3$ ; Height of fill above top of pipe =  $2.5 \text{ m}$ ;  $Pr_s = 0.7 \times 0.7 = 0.49$  (say  $0.5$ )

From Table 14 for  $D = 750$  mm and height =  $2.5$ ; Load on pipe =  $67 \text{ kN/m}$ ; Applying density correction,  $W = 67(1600/2000) = 53.6 \text{ kN/m}$ . Since  $Pr_s = 0.5$  and the value of load falls to the right of the heavy line, actual load on pipe is:  $W = 53.6 \times 0.95 = 50.9 \text{ kN/m}$

#### 4.2.3. Induced Trench Installation


The induced trench installation is a special technique used to increase the height of the fill that can be carried by standard strength conduits under very high embankments (see Figure 15(a)). The procedure followed is to:

- Install the conduit as normally done in an embankment installation
- Backfill over it to the required height
- Dig a trench of the same width as the outside dimension of the conduit down to  $\pm 300\text{mm}$  from the top of the conduit
- Fill the sub-trench with a compressible material as straw or sawdust
- Complete backfilling up to formation level as for a standard embankment installation.

The yielding material in the sub-trench settles and thus produces frictional forces that reduce the load on the conduit. The deeper the sub-trench the higher the frictional forces developed and hence the greater the reduction in load to be carried by the conduit.

Under very high fills, where standard pipe/bedding class combinations or portal culvert classes are inadequate

to cope with the earth loads standard product classes are used and the sub-trench depth is adjusted to reduce the load to the required value. An important fact to appreciate with this type of installation is that the settlement in the sub-trench must not be so great that the top of the formation settles. In other words there must be sufficient fill over the conduit to allow a plain of equal settlement to form below the top of the formation. Details of this are shown in Figure 17(a) below



#### 4.2.4. Jacked Installation

When conduits are to be placed under existing roadways, railways or other areas that are already developed trench digging can be extremely disruptive and the indirect costs enormous. An alternative to this is the jacking installation technique.

When a conduit is jacked the mass of the earth above the pipe is reduced by both friction and cohesion that develop between the columns of earth directly on top of the conduit and those columns of earth either side of it.

This technique involves:

- Excavating a pit at the beginning and end of the proposed line.
- Constructing a launching pad in the entry pit
- Pushing a jacking shield against the face of the pit
- Tunnelling through the soil while being protected by the jacking shield by making an excavation slightly larger than the shield just ahead of it
- Pushing conduits into the tunnel as it progresses
- Grouting the space left between the outside of the conduit and the tunnel.

With a jacked installation the vertical load on the conduits will be significantly less than that experienced in a trench installation. This is because the load is dependant on the outside dimension of the conduit and not the trench width and as the soil above the conduits is undisturbed the load is reduced by both cohesion and friction. Once the fill height over the conduit exceeds about 10 times its outside width full arching will take place and no matter how much higher the fill there will be no further increase in the load that the conduit has to carry.

### 4.3. TRAFFIC LOADING

Where conduits are to be installed under trafficked ways details of the vehicles using them should be determined in terms of:

- Axle spacing and loads
- Wheel spacing, loads and contact areas

The type of riding surface and height of fill over the conduits should also be determined.

Most concrete pipes and portals that are subject to live loads are those used under roads. In this handbook two types of design vehicle have been considered, namely a typical highway vehicle that has two sets of tandem axles and the NB36 vehicle, associated with abnormal loads on national highways (as described in TMH7). As the typical highway vehicle may be overloaded or involved in an accident it is not suitable as a design vehicle under public roads. The design loads as given in TMH7 should be used for the design of all structures under major roads. Under most conditions the loading from the NB36 vehicle is the most critical for buried storm water conduits. The typical legal vehicle would be used for the design of conduits in areas outside public




jurisdiction. The most severe loading will occur when two such vehicles pass, or are parked next to each other. Figure 18 illustrates the wheel configuration of these vehicles.

When the effect of these loads is considered on buried conduits an allowance for impact for impact should be made. For the typical highway vehicle this is usually taken as 1.15. Where greater impact is expected due to a combination of high speed, rough surface and

hard suspension, an impact factor up to 1.4 could be applied. The effective contact area for these wheels is taken as 0.2 m x 0.5 m in direction of and transverse to direction of travel respectively.

The loads on pipes due to 40 kN wheel loads with the configuration shown in Figure 16(a) are given in Table 15. The table can be used for any wheel load (P) provided that the wheel arrangement is the same and the load multiplied by P/4.

Figure 18: Traffic loading on roads



For the NB loading, 1 unit = 2.5 kN per wheel = 10 kN per axle and = 40 kN per vehicle.  
For the NB36 vehicle = 90 kN per wheel = 360 kN per axle.

TABLE 15: LOADS IN KN/M ON BURIED CONDUIT FROM GROUP OF 40 KN WHEELS

Pipe ID	Fill height over pipes in m										
	0.6	1.0	1.5	2.0	2.5	3.0	3.5	4.0	5.0	6.0	7.0
300	8.1	4.78	2.8	1.8	1.3	1.0	0.7	0.6	0.4	0.3	0.2
375	10.2	5.97	3.5	2.3	1.6	1.2	0.9	0.7	0.5	0.3	0.2
456	12.2	7.16	4.2	2.8	2.0	1.5	1.1	0.9	0.6	0.4	0.3
525	14.2	8.36	4.9	3.3	2.3	1.7	1.3	1.0	0.7	0.5	0.4
600	16.3	9.55	5.7	3.7	2.7	2.0	1.5	1.2	0.8	0.6	0.4
675	18.3	10.7	6.4	4.2	3.0	2.2	1.7	1.4	0.9	0.6	0.5
750	20.4	11.9	7.1	4.7	3.3	2.5	1.9	1.5	1.0	0.7	0.5
825	22.4	13.1	7.8	5.2	3.7	2.7	2.1	1.7	1.1	0.8	0.6
900	24.5	14.3	8.5	5.6	4.0	3.0	2.3	1.8	1.2	0.9	0.7
1 050	28.5	16.7	9.9	6.6	4.7	3.5	2.7	2.1	1.4	1.0	0.8
1 200	32.6	19.1	11.4	7.5	5.3	4.0	3.1	2.5	1.7	1.2	0.9
1 350	38.3	22.4	13.3	8.8	6.3	4.7	3.6	2.9	1.9	1.4	1.0
1 500	42.6	24.9	14.8	9.8	7.0	5.2	4.0	3.2	2.2	1.6	1.2
1 650	46.8	27.4	16.3	10.8	7.7	5.7	4.4	3.5	2.4	1.7	1.6
1 800	51.1	29.9	17.8	11.8	8.4	6.3	4.9	3.9	2.6	1.9	1.4

Notes:

1. No impact factor has been included.
2. Impact should certainly be considered for low fills (< diameter of pipe).
3. The tables do not apply to pipes on concrete bedding.
4. Where the cover over the pipe is less than half the outside pipe diameter the bedding factor for the live load must be reduced. Special precautions as concrete encasement may be necessary.

The loads given in TMH7 for the design of structures under major roads are:

- Normal loading (NA)
- Abnormal loading (NB)
- Super loading (NC)

As stated above the NB36 loading is usually the critical one for buried conduits. TMH7 allows an equivalent point load to be used for NB loading that is dependant upon the outside width and length of the conduit. For the NB36 loads this is expressed as:

$$Q_b = 1.25(90 + 12L_s^{1.8})$$

Where  $Q_b$  - equivalent point load  
 $L_s$  - effective span of conduit in m

**TABLE 16: LOADS IN KN/M ON BURIED PIPES FROM NB36 GROUP OF WHEELS**

PIPE ID	PIPE OD	FILL HEIGHT OVER PIPES IN M											NB36 PT LOAD
		0.6	1.0	1.5	2.0	2.5	3.0	3.5	4.0	5.0	6.0	7.0	
300	0.345	26	12	7	4	3	2	1	1	1	1	0	114
375	0.431	31	15	8	5	3	2	2	1	1	1	0	115
456	0.518	35	17	10	6	4	3	2	2	1	1	1	116
525	0.604	39	19	11	7	5	3	2	2	1	1	1	117
600	0.690	43	22	12	8	5	4	3	2	1	1	1	118
675	0.776	46	24	14	9	6	4	3	2	2	1	1	120
750	0.863	49	25	15	9	6	5	4	3	2	1	1	121
825	0.949	52	27	17	10	7	5	4	3	2	1	1	123
900	1.035	55	29	18	11	8	6	4	3	2	2	1	125
1 050	1.208	60	33	21	13	9	7	5	4	3	2	1	129
1 200	1.380	64	36	24	15	10	8	6	5	3	2	2	133
1 350	1.620	67	40	28	18	12	9	7	5	4	3	2	138
1 500	1.800	67	43	31	20	14	10	8	6	4	3	2	144
1 650	1.980	68	46	34	22	15	11	9	7	5	3	3	149
1 800	2.160	69	49	37	24	17	13	10	8	5	4	3	156

Notes

1. The NB36 vehicle travels slowly and generally no impact needs to be considered.
2. Under certain conditions the NB24 vehicle could be used for minor roads.


## 5. CONCRETE PIPE STRENGTHS

### 5.1. EXTERNAL LOADS

The size of circular pipes is defined by one dimension only. This simplifies the relationship between the load to

be carried and the strength required to do so. For rigid pipes as concrete the strength is usually determined by using what is called the direct method.

Using the information from the previous sections the required concrete pipe strength can be determined by dividing the installed load by a bedding factor. Factory test loads and reactions are concentrated. The field loads and reactions have a parabolic or radial distribution around a



pipe. However it is assumed that the loads are uniformly distributed over the pipe and that the bedding reactions have either a parabolic or uniform distribution dependant upon the bedding material used. A comparison of these loads and reactions is shown in Figure 19.

Bedding factors have been derived for standard bedding classes and are described in detail in Section 6 that follows. The bedding factors for a trench installation assume that there is a vertical reaction only and no lateral support to the pipe. For an embankment installation lateral support is taken into account and hence the embankment bedding factors are somewhat higher than those used for a trench installation. For most installations the bedding factors given in Table 17 below are adequate.

**TABLE 17: BEDDING FACTORS FOR CONCRETE PIPE**

Bedding details			Installation details	
Class	Material	Angle	Trench	Embankment
A	Reinforced concrete	180	3.4	4.8
A	Concrete	180	2.6	3.9
B	Granular	180	2.0	2.4
C	Granular	60	1.5	2.0
D	Granular	0	1.1	1.2

**Note:**

- 1) Class D bedding should only be used when suitable bedding material is not available.
- 2) Class A bedding should not be used unless there are special requirements to be met.
- 3) For zero and negative projection installations use trench bedding factors.

For positive projection conditions, where greater accuracy is required the bedding factors can be calculated using the procedure described in Section 6.

**5.2. INTERNAL PRESSURE**

Where a pipeline is required to work under internal pressure, two conditions must be considered:

- The static head of water in the pipe, excluding the losses due to friction.
- Dynamic factors that can cause pressure surges above and below the static or working head.


The factors to be considered are:

- Whether or not the flow can be unexpectedly stopped and if so whether the stoppage is gradual or instantaneous
- Whether the surges below the working head can give rise to negative pressures.

For pressure pipes a factor of safety of 1.5 is normally used where only the working pressure is known. Where the pressures along the pipeline have been accurately calculated, taking into account surge and water hammer effects, the line is usually divided into pressure zones or reaches. The factor of safety at the lowest section of any zone is usually taken as 1.0.

When concrete pipes are used for a pressure pipeline it is usually a gravity system or a siphon where surges cannot develop. Hence specifying a factory hydrostatic test pressure that is 1,5 times the maximum static or operating head is adequate.

Figure 19: Factory strength as model of installed load on pipe



a) Three edge bearing test

b) Uniform reaction

c) Parabolic reaction

### 5.3. SAFETY FACTORS

The choice and application of safety factors is left to the discretion of the designer. It is suggested that either each load be considered independently and a factor of safety ranging from 1.0 to 1.5, applied directly to the value of the load, or the required pipe strength. Recommended values are given in Table 18.

The determination of a factor of safety to be used in designing a pipe depends on:

- Field working conditions
- Degree of supervision
- Height of fill above a pipe
- Whether or not there are corrosive elements in the transported fluid, or the groundwater.

**TABLE 18: RECOMMENDED SAFETY FACTORS FOR VERTICAL LOADS ON CONCRETE PIPES**

Pipe Application	Factor of safety	
	Reinforced	Non-reinforced
Storm water drainage	1.0	1.3
Sewer pipes without sacrificial layer	1.3	1.7
Pipes laid in corrosive ground condition	1.3	1.7
Sewer pipes with sacrificial layer	1.0	1.3

### 5.4. SELECTION OF THE CONCRETE PIPE CLASS

As the size of circular pipes is defined by one dimension only, the relationship between the load to be carried and the pipe strength required, is simplified. The strengths can be determined by using an indirect approach. This means that the installed loads are connected into a factory test load by using a bedding or safety factor.

#### 5.4.1. External load

The relationship between the factory test load and installed field load is given by the equation developed by Marston and Spangler, namely:

$$W_T = W_I FS/B_F$$

Where  $W_T$  - required proof load for 0.25 mm crack  
 $W_I$  - external load (kN/m)  
 $FS$  - factor of safety  
 $B_F$  - bedding factor

The pipe class is selected so that:

$$W_T < S$$

Where  $S$  - proof load of a standard D-load class pipe (kN/m)

#### 5.4.2. Internal pressure

The selection of the pressure class is made as follows:

$$t = p \times FS$$

Where  $t$  - required test pressure (kPa)  
 $p$  - design pressure in pipeline  
 $FS$  - factor of safety

The pipe class is selected so that

$$t < T$$

Where  $T$  - test pressure of standard pressure class pipe (kPa)

#### 5.4.3. Combined internal pressure and external load

Where pipes are to be subjected to combined external load and internal pressure the following formula is used for pipe selection:

$$T = t / [1 - (W_T/S)^2]$$


When selecting a pipe for these conditions, a balance between  $T$  and  $S$  should be found. A pipe should not be selected that is required to withstand a very high pressure and a very low vertical load or vice versa, as such a pipe would be uneconomical.

#### Example 1

Determine the strength of a 900mm internal diameter storm water pipe under the following conditions: Trench installation, using trench width in accordance with SANS 1200 DB. Backfill material: dry sand ( $w = 1\ 600\text{kg}/\text{m}^3$ ). Height of fill on top of pipe: 3.5m. Traffic loading: NB 36. Bedding: Class B. Pipeline in corrosive soil conditions.

From Table 8, load due to fill =  $(1600/2000) \times 84 = 67.2\ \text{kN}/\text{m}$  and from Table 11 NB 36 loading =  $4.0\ \text{kN}/\text{m}$

Since pipe is in corrosive conditions a safety factor of 1.3 should be applied to total load. The class B bedding factor is 2.0, therefore required minimum proof load,  $S$  will be:



$$W_T = ((\text{earth load} + \text{live load}) \times \text{SF}) / \text{BF}$$

$$= ((67.2 + 4) \times 1.3) / 2.0 = (71.2 \times 1.3) / 2.0 = 92.6 / 2.0 = 46.3 \text{ kN/m}$$

A class 75 D (67.5 kN/m proof load) will therefore be adequate. If an economic evaluation of the installation is required the pipe bedding class combinations that are adequate as well as their costs are needed so that the total cost can be calculated.

Bedding Class	Bedding Factor	Required Test	Required D-Load	Standard D-load
C	1.5	61.7	68.6	75
B	2.0	46.3	51.4	75
A non reinforced	2.6	35.6	39.6	50
A reinforced	3.4	27.2	30.3	50

#### Example 2

Determination of strength of a 1 200 mm internal diameter pipe culvert to be installed under the following conditions: Embankment installation Positive projection: projection ratio  $p = 0.7$  Foundation material: rock ( $r_s = 1$ ) Height of fill above top of pipe: 2.5 m Backfill density: 1 650 kg/m<sup>3</sup>. Light traffic conditions are expected, assume 4 000 kg maximum wheel load Class B bedding Non-corrosive conditions

For a value of  $P r_s = 0.7 \times 1.0 = 0.7$ , Table 10 gives a backfill load =  $(1650/2000) \times 147 = 121.3 \text{ kN/m}$  and from Table 12 traffic load = 4.1 kN/m. The factor of safety is 1 (See 4.6)

The required proof load, will be:

$$W_T = ((\text{earth load} + \text{live load}) \times \text{SF}) / B_f = ((121.3 + 4.1) \times 1) / 2.4 = 52.3 \text{ kN/m}$$

A class 50D pipe (60 kN/m load should be specified.

#### Example 3

A 300 mm internal diameter pressure pipeline is to be installed in a trench under the following conditions: The maximum pressure expected in the line including surge and water hammer is: 150 kPa Trench width : 900 mm Height of fill: 1.5 m Material: wet sand (density 2 000 kg/m<sup>3</sup>) Bedding: Class C Non-corrosive conditions From Table 4 for trench width 900 mm and height 1.5 m; Load on pipe = 20 kN/m Class C bedding factor = 1.5 and Factor of safety = 1.0 (See section 4.6)

Required pipe strength

$$W_T = ((20 / 1.5) \times 1 = 13.3 \text{ kN/m}$$

Assume a Class 50D pipe is used (15 kN/m proof load). To determine the minimum resistance to internal hydraulic pressure, the following formula is applied:

$$T = t / (1 - (W_T / S)^2) \quad (\text{see Par 4.7.3})$$

where  $t = 150 \text{ kPa}$ ,  $W_T = 13.3 \text{ kN/m}$  and  $S = 15.0 \text{ kN/m}$

$$\text{Therefore } T = 150 / (1 - (13.3 / 15)^2) = 700 \text{ kPa}$$

The pipe specification should be Class T 8 (test pressure 800 kPa) and Class 50D.

Alternative classes could be determined by starting with a 100D pipe (30 kN/m)

$$T = 150 / (1 - (13.3 / 30)^2) = 187 \text{ kPa}$$

In this design the pipe specification would be T2 (200 kPa) and Class 100D that would probably be more economic than the first alternative.


## 6. BEDDING

### 6.1. GENERAL

The bedding supporting a pipe transfers the vertical load on the pipe to the foundation. It also provides a uniform support along the pipeline and prevents any load concentrations on the pipe due to irregularities in the foundation. The ability of a rigid pipe to carry field loads that are larger than the test load depends on the degree of support given to the pipe by the bedding. The ratio between the load that a pipe can support on

a particular type of bedding, and the test load is called the bedding factor.

When selecting granular materials for Class B, C and D beddings the designer must consider the interface between the bedding material and the surrounding natural material. Precautions must be taken to prevent the ingress of fine material into the bedding layer, as this will result in a loss of support to the pipe.



## 6.2. TRENCH AND NEGATIVE PROJECTION INSTALLATIONS

### 6.2.1. General


The pipe weight and the loads on it are transferred to the foundation through the bedding. The amount the


bedding yields under this load determines the pressure distribution of the reaction between bedding and pipe. For trench installations no allowance is made for lateral earth pressure. Pressures are assumed to act on the pipe in the vertical direction only.

Loose granular beddings are flexible and will yield more than a pipe deforms under load. The pressure distribution of the reaction from this type of bedding is parabolic. A rigid bedding with the same flexural stiffness as the pipe will deform the same amount as the pipe under load and the pressure distribution of reaction between pipe and bedding will be rectangular and uniform. Figure 21 gives the relationship between the bedding factor and the angle of bedding support for uniform and parabolic reactions. The maximum bending moment occurs at the invert of the pipe under these loading conditions.


In negative projection installations, where the limits are the trench condition and the zero friction condition, the development of lateral soil pressures is ignored, as it is difficult to obtain adequate compaction of the backfill in confined spaces.

Where the design corresponds to one of the bedding classes given below, the bedding factor for that class should be used. The key to the materials used is given in Table 19 over the page. Alternatively, Figure 21 may be used to obtain an appropriate bedding factor.





**TABLE 19: KEY TO MATERIALS USED**



- (a) Institutional Material
- (b) Main backfill
- (c) Loose backfill
- (d) Lightly compacted backfill
- (e) Densely compacted backfill
- (f) Reworked foundation
- (g) Selected granular material
- (h) Fine granular material
- (i) Compacted granular material


**6.2.2. Class A beddings**

The concrete beddings commonly used are given in Figure 22. The bedding width shall not be less than  $B_c + 200$  mm but may extend the full width of the trench. Steel reinforcement if used must not be less than 0.4 % of the concrete cross-section and must be placed transversely beneath the pipe and as close to it as possible allowing for the minimum cover required for reinforced concrete. The concrete shall have a 28-day cube strength of not less than 20 MPa.

The class A bedding factors are:

Unreinforced	0.4% Reinforcement	1.0% Reinforcement
2.6	3.4	4.8

Figure 23: Class A trench beddings over pipes



When Class A bedding is placed over/under pipes it should have a minimum thickness of  $B_c/4$ . If this cannot be achieved then the concrete should be reinforced.

These factors are slightly higher than the values given in Figure 21 as it is assumed that the Class A concrete bedding is stiffer than the pipe it supports. As a result the pressure under the pipe will have an inverse parabolic distribution, giving a lower bending moment at the pipe invert than the uniform distribution.

Figure 22: Class A trench beddings under pipes



(a) Class A (non-reinforced)

(b) Class A (reinforced)

(c) For Wet Conditions

### 6.2.3. Class B Beddings

The Class B Granular bedding commonly used is shown in Figure 24(a). The bedding angle is  $180^\circ$  and the pressure distribution under the pipe is assumed to be parabolic. The selection, placement and compaction of the granular material must be carried out so that this assumption is not compromised.

The construction detail of the shaped sub-grade bedding with a granular curtain is shown in Figure 24(b). The width of the bedding is  $0.7 B_c$  ( $90^\circ$  bedding angle) and the pressure distribution under the pipe is assumed to be uniform. The depth of the fine granular blanket must not be less than 50 mm and the side fill must be well compacted.

The Class B bedding factors are:

Granular Bedding	Shaped Sub-grade	Fully Encased
2.0	2.0	2.2

### 6.2.4. Class C beddings

A reduced bedding factor is assumed, to allow for a poorer quality of bedding cradle material and compaction and a smaller bedding angle than used with Class B beddings. The selection, placement and compaction of the granular material must be carried out so that this assumption is not compromised. Details are given in Figure 25 below.

When a granular cradle is used the bedding angle is  $90^\circ$  and the pressure distribution is assumed to be parabolic.

The construction detail of this shaped sub-grade bedding is shown in Figure 25(b). The bottom of the trench is compacted, levelled and shaped so as to support the pipe barrel over a width of  $0.5 B_c$  ( $60^\circ$  bedding angle). No blanket is provided and the backfill around the pipe is lightly compacted.

The construction detail of the flat granular bedding is shown in Figure 25(c). It is assumed that the pipe

Figure 24: Class B trench beddings






Figure 25: Class C beddings





barrel penetrates the bedding material to achieve a support angle of at least 45° with a uniform pressure distribution under the pipe. A suitable material for this type of bedding is a single sized gravel or aggregate consisting of rounded particles that can flow easily. Crushed aggregates containing a high percentage of angular particles, are more stable and will minimise the settlement of the pipe into the bedding material. It is important that the properties of the material are matched to the size and acceptable settlement of the pipe.


The bedding factors for Class C granular beddings are:

Granular support angle 60°	Shaped sub-grade	Uncompacted granular	Granular support angle 90°
1.5	1.5	1.5	1.7


### 6.2.5. Class D beddings

No special precautions are required for this class of bedding except that the sub-grade must fully support the pipe in the longitudinal direction and that holes must be excavated in the floor of the trench to accommodate sockets or joints that have a diameter greater than that of the pipe barrel. Load concentrations on the pipe must be avoided. This class of bedding is not suitable in situations where the founding conditions consist of very hard or very soft insitu material such as rock, hard gravel or soft clay.

Figure 26: Class D trench beddings



(a) Flat sub-grade



(b) Compacted granular material

The construction detail of the flat sub-grade bedding is shown in Figure 26(a). Where the flat sub-grade surface is not suitable as bedding it should be improved by compacting and levelling a layer of suitably graded granular material. This layer will provide uniform support along the length of the pipe, without the risk of load concentrations occurring (see Figure 26(b)). The type D beddings should only be used for smaller diameter pipes where the pipe cost is much less than the total installation cost. The bedding factor for class D beddings in a trench or negative projection installation is 1.1

## 6.3. POSITIVE PROJECTION INSTALLATIONS

### 6.3.1. General

In positive projection installations, where the limits are the zero friction or geostatic condition and the complete projection condition, active lateral soil pressures develop in the fill and these help to carry the vertical load on the pipe. The bedding factors used for these installations are therefore higher than those used for trench and negative projection installations. The bedding classes are the same as those used in negative projection installations. The enhanced values of the bedding factors as given below are determined by using Spangler's method.

### 6.3.2. Spangler's Method

The bedding factor applicable to positive projection installations is calculated using formula below.

$$B_f = \frac{A}{N - (x \cdot q)}$$

where A - 1.431 for circular pipes

N - is obtained from Table 14

x - is obtained from Table 15

q - is calculated from formula below

$$q = \frac{mK}{C_c} \times \frac{H}{B_c} + \frac{m}{2}$$

Where q - ratio of total lateral pressure to total vertical load

K - Rankine's coefficient of active earth pressure, usually taken as 0.33

C<sub>c</sub> - fill load coefficient for positive projection

m - proportion of B<sub>c</sub> over which lateral pressure is effective. See Figure 22.

H - fill height over pipe

**TABLE 20: VALUES OF N FOR POSITIVE PROJECTION BEDDINGS**

Type of bedding	Value of N
Class A – restrained	0.421
Class A – unrestrained	0.505
Class B	0.707
Class C	0.840
Class D	1.310

Note: Reinforced or plain concrete beddings cast against stable rock, are restrained


**TABLE 21: VALUES OF x FOR POSITIVE PROJECTION BEDDINGS**

Value of m	Concrete	Other
0.0	0.150	0.000
0.3	0.743	0.217
0.5	0.856	0.423
0.7	0.811	0.594
0.9	0.678	0.655
1.0	0.638	0.638

Note: The parameter x is a function of the proportion of the pipe over which active lateral pressure is effective.

The standard embankment bedding details are shown in Figures 27 and 28.

Figure 28: Embankment Class D beddings




#### 6.4. SOILCRETE BEDDING

Soilcrete or soil-cement as it is sometimes called is an alternative bedding material that is used under certain circumstances such as when there are:

- concerns about bedding material washing away and causing piping next to pipeline
- time restraints on the installation
- trenches that are narrow and side compaction is difficult.

Figure 27: Embankment Class A, B and C beddings







Figure 29: Use of soilcrete around pipes



(a) Soilcrete as gap filler

(b) Soilcrete as bedding

Soilcrete consists of a granular material that has between 3% and 6% of cement added to it and is made as a flowable mix with a slump of >200mm. There should be no organic material in the soil used and ideally the clay content should be minimal. The soilcrete is stronger than soil, having a strength between 0.5 and 1.0 MPa. This material can be used in two ways, namely as a gap filler or as a bedding as illustrated in Figures 29 (a) and (b).

The purpose of the Soilcrete is to transfer the load on the pipe to the surrounding soil. As it is stronger than soil it does not matter if there are small cracks in it. The important issue is that the material is stable and supports the pipes. To ensure that there is support all around the pipe this material needs to be flowable and vibrated once placed. To prevent floatation the soilcrete is placed in two stages, the first should not be higher than  $\pm$  a sixth of the pipe OD. The second stage can be placed as soon as the initial set has taken place. (When a man can walk on it.) for installation details reference should be made to the Installation Manual that is a companion publication to this one.

When soilcrete is used as a gap filler the distance between the pipe and excavated material should be  $\pm$  75 mm. When it is used as bedding the dimensions should be the same as those used for concrete bedding. The bedding factors for soilcrete beddings will depend on the bedding angle and can be taken from the curve for concrete on Figure 21.

## 6.5. JACKING CONDITIONS

When the pipes are jacked the excavation is slightly larger than the external diameter of the pipe. However, the process of installing a pipe ensures that positive contact is obtained around the bottom portion of the pipe and that ideal bedding conditions are obtained. If the pipe carries

all or part of the vertical earth load, the use of the trench bedding factors is appropriate. These will depend on the width of contact between the outside of the pipe and the material through which the pipe is being jacked. As this will usually be at least  $120^\circ$  a value of 1.9 can be used.


When determining the bedding factor, the behaviour of the insitu material after the jacking is completed and the post installation treatment given to the void between the pipe and the excavation should be considered. If this is grouted, a value of 3 can be used.

## 7. PIPE JOINTING

### 7.1. JOINT TYPES

The function of the joint is to provide flexibility and sealing for the pipeline. Joints are designed to cope with the movement that occur due to the secondary forces within the soil mass. There are four types of pipe joints, namely, butt (or plain ended), interlocking (or Ogee), spigot and socket and in-the-wall joints. These are used for different applications that are determined by the amount of movement to be tolerated and the importance of keeping the pipeline sealed.

Figure 30: Joint types for concrete pipe



(a) Butt

(b) Interlocking

(c) Spigot and socket

(d) In-the-wall

## 7.2. BUTT AND INTERLOCKING JOINT PIPES

Butt ended and interlocking pipe joints are not intended to prevent infiltration and exfiltration of water hence they are only used for stormwater drainage and culvert pipe. Butt ended pipes are seldom used as they do not have any means of self-centering when being jointed.

If there is a potential problem with the loss of bedding material into the drainage system the joints should be sealed either with mortar or sealing tape. When stormwater drains are placed on steep slopes and the flow velocity exceeds 4 or 5 m/s it is advisable to use one of the joints that can be sealed with a rubber ring to prevent the high velocity water going through the joints and scouring cavities in the soil around the pipes.

Pipes for sewers or pressure pipelines should have spigot and socket or in-the-wall joints that include seal in the form of either a rolling ring or confined ring.

## 7.3. SPIGOT AND SOCKET JOINTS

Pipes with this joint type are the most commonly used for sewers. They are designed to seal as well as tolerate movements in three directions, namely:

- Draw or longitudinal movement.
- Deflection or radial movement.
- Relative settlement or displacement of a pipe relative to the adjacent ones.

In addition to this these joints take into consideration tolerances on concrete surfaces, laying procedures and seal dimensions. The rubber ring enables this type of joint to be deflected as shown in Figure 31 so that pipes can be laid around curves and still remain watertight.

The amount of movement that can be tolerated at a joint will depend on the pipe size and the manufacturer's details. The radius of the curve is dependent on the

angular deflection that is permitted for each pipe size. Typical deflections and curve radii are given in Table 22. Specific projects should be discussed with the manufacturer concerned.

**TABLE 22: ANGULAR DEFLECTIONS AND CURVE RADII**

Nominal Pipe Diameter - mm	Permissible Degrees	Minimum Radius - m
300 - 375	2.00	70
450 - 600	1.50	93
675 - 900	1.00	140
1 050 - 1 200	0.75	186
1 350 - 1 800	0.50	280

The radius of curve that can be negotiated is directly proportional to the pipes' effective length. The values in this table were calculated using an effective pipe length of 2.44m. If a different length is used the radius from the table should be corrected by the ratio of the lengths. Where sharp curves in excess of these values are required special pipes with deflected spigots or sockets, or radius pipe can be produced. This should be discussed with the manufacturers.


When a curve is being negotiated, the pipes must first be fully jointed in a straight line and only then deflected.


The spigot and socket pipe has traditionally been made with a rolling rubber ring. The South African standard for rubber rings is SANS 974-1: Rubber joint rings (non-cellular) Part 1: Joint rings for use in water, sewer and drainage systems.

## 7.4. IN-THE-WALL JOINTS

With large diameter pipes the wall is so thick that a rubber ring joint can be accommodated within the wall thickness. With this type of joint nibs on the jointing surfaces or a

Figure 31: Angular deflection of spigot and socket pipes





groove in the spigot confine the seal. As the seal remains in a fixed position the socket slides over this so both the seal and the socket of the pipe to be jointed should be thoroughly lubricated before the joint is made. This type of joint is sometimes called a confined or sliding rubber ring joint. Particular attention should be paid to lubricating the lead-in section of the socket that makes the first contact with the seal.

The advantage of this type of joint is that the outside diameter of the pipe remains constant making the pipe ideally suited for jacking. For jacking pipes from 900 mm in diameter and larger use this joint type. However for sewers this type of joint is seldom used for pipes of less than 1500 mm in diameter. Most pipes larger than 1800 mm in diameter are made with this type of joint.

The joint is designed to cope with the same criteria as the spigot and socket joint, but as it is shorter than the spigot and socket joint the amount of movement that it can tolerate will in general be a little less. These joints can, in general, cope with a deflection of 0.5 degrees and be used to negotiate curves if required to do so.

For details of how pipes should be jointed the reader is again referred to the Concrete Pipe and Portal Culvert Installation Manual or the pipe supplier.

## 8. FLOATATION

### 8.1. GENERAL

Any buried pipeline, even when full of water will weigh less than the soil that it displaced. Hence there will be a tendency for pipelines to lift rather than settle. When the groundwater level is higher than the bottom of the pipeline the buoyancy forces can lift the pipeline due to. If these conditions can occur either during the installation or operation of the pipeline the designer should check that the pipeline will not float off its bedding.

SANS 10102 Part 2 lists several conditions that could give rise to this, namely:

- Flooding of trench to consolidate backfill
- Pipelines in flood plains or under man-made lakes that will be below groundwater level
- Sub aqueous pipelines
- Pipelines in other areas that may be subject to a high water table

If any of these exist the designer should calculate the forces to establish whether or not floatation will be a problem. These forces are:

- Weight of pipe
- Weight of water displaced by pipe
- Weight of load carried in pipe
- Weight of any backfill over the pipe

Two floatation conditions can occur, namely:

- Pipeline is submerged partly or fully before backfilling
- Pipeline becomes submerged after backfilling

### 8.2. FLOATATION BEFORE BACKFILLING

The weight of the displaced water in kN/m of pipeline,  $ww$  is calculated from:

$$ww = \gamma_w L_1 A_1$$

- $\gamma_w$  - density of water in kN/m<sup>3</sup>
- $L_1$  - length of pipeline in m
- $A_1$  - cross-sectional area of pipeline below water surface in m<sup>2</sup>

The pipeline will float if

$$ww > wp$$

$wp$  - the pipeline mass in kN/m

### 8.3. FLOATATION AFTER BACKFILLING

The vertical soil load acting on the pipeline in kN/m of length,  $wb$  can be calculated from:

$$wb = \gamma' Bc H$$

- $\gamma'$  - submerged density of saturated backfill in kN/m<sup>3</sup>
- $Bc$  - outside diameter of pipeline in m
- $H$  - fill height over pipeline in m

$$\gamma' = \gamma_w - (G_1 - 1)/(1 + e)$$

- $G_1$  - specific gravity of soil particles
- $e$  - void ratio of soil

The pipeline will float if


$$ww > wp + wb$$

## 9. SEWER CORROSION

### 9.1 CORROSION MECHANISM

Concrete is the most frequently used material for the manufacture of outfall sewers. Under certain conditions concrete sewers may be subject to corrosion from sulphuric acid ( $H_2SO_4$ ) formed as a result of bacterial action. The physical appearance of corrosion is first detected as a white efflorescence above the water line, and it takes several months before this starts. Thereafter deterioration may be rapid in which case the concrete surface becomes soft and putty-like and there is aggregate fallout.

There are three sets of factors contributing to this phenomenon, those resulting in the generation of the gas hydrogen sulphide ( $H_2S$ ) in the effluent those resulting in the release of  $H_2S$  from the effluent and those resulting in the biogenic formation of  $H_2SO_4$  on the sewer walls. These are illustrated in figure 32 below.



The most important factors contributing to  $H_2S$  generation in the effluent are:

- Retention time in sewer
- Velocities that are not self cleansing
- Silt accumulation
- Temperature
- Biochemical oxygen demand (BOD)
- Dissolved oxygen (DO) in effluent
- Dissolved Sulphides (DS) in effluent
- Effluent pH.

The most important factors contributing to  $H_2S$  release from the effluent are:

- Concentration of  $H_2S$  in effluent
- High velocities and turbulence

The most important factors contributing to  $H_2SO_4$  formation on the sewer walls are:

- Concentration of  $H_2S$  in sewer atmosphere
- Rate of acid formation
- Amount of moisture on sewer walls
- Rate of acid runoff


If there is insufficient oxygen in the effluent the bacteria that live in the slimes layer on the sewer walls strip the oxygen from the sulphates in the effluent to form sulphides. The first set of factors influence the rate at which this occurs. When there is an imbalance of  $H_2S$  in the sewage and the sewer atmosphere this gas will come out of solution so that there is equilibrium. The second set of factors influence this. The  $H_2S$  released into the sewer atmosphere is absorbed into the moisture on the sewer walls and is oxidised by another set of bacteria to  $H_2SO_4$ . This is influenced by the third set of factors.

The acid formed then attacks the cement in the concrete above the water line, as it is alkaline. If an inert aggregate is used there is aggregate fallout when the binder corrodes. This exposes more of the binder that in turn is corroded by the acid. The deterioration of the pipe wall is rapid. If concrete is made using a calcareous aggregate, which is alkaline, the acid attack is spread over both binder and aggregate, the aggregate fallout problem is minimised and the rate at which the sewer wall deteriorates is reduced.

### 9.2. CORROSION PREDICTION AND CONTROL

Research by Pomeroy and Kienow <sup>[9]</sup> led to the development of a quantitative method for predicting the rate of sulphide generation and the resultant rate of concrete corrosion. This later became known as the Life Factor Method (LFM). In 1984 the American Concrete Pipe Association (ACPA) published the "Design Manual Sulfide and Corrosion Prediction and Control"<sup>[9]</sup>. This quantified the LFM <sup>[10]</sup> by giving equations for predicting the corrosion in concrete sewers based on the biological composition of the effluent, the system hydraulics and the alkalinity of the concrete used. The final output is the required additional cover to reinforcement, referred to as "sacrificial layer" in South Africa, for a concrete pipe to ensure that it will remain serviceable for its design life.

The theoretical prediction of  $H_2S$  generation in the sewerage is based on an analysis of the effluent and is beyond the scope of this document. If the reader requires the procedure reference should be made to reference 10. Once the DS in the effluent has been



determined the rate of  $H_2S$  release from effluent, called the  $H_2S$  flux can be calculated from:

$$\varnothing_{sf} = 0,69 (sv)^{3/8} J [DS] \quad (1)$$

$\varnothing_{sf}$  -  $H_2S$  flux from stream surface,  $g/m^2/h$

$s$  - energy gradient of wastewater stream,  $m/m$

$v$  - stream velocity,  $m/s$

$J$  - fraction of  $DS$  present as  $H_2S$  as function of  $pH$

$\varnothing_{sf}$  - average annual dissolved sulphide concentration in wastewater,  $mg/l$  ( $0,2$  to  $0,3$   $mg/l$  less than the total sulphide concentration)

The absorption of this  $H_2S$  into the moisture layer on the wall of the sewer is determined from a modification of the above equation:

$$\varnothing_{sw} = 0,69 (sv)^{3/8} J [DS] (b/P') \quad (2)$$

$\varnothing_{sw}$  -  $H_2S$  flux to the pipe wall,  $g/m^2/h$

$b/P'$  - ratio of wastewater stream width to perimeter of pipe wall above water surface.

This assumes that all the  $H_2S$  that is released is absorbed into the moisture layer.

The concrete corrosion rate can be estimated by calculating the rate at which the  $H_2S$  flux to the pipe wall will be oxidised to  $H_2SO_4$ .  $34g$  of  $H_2S$  are required to produce sufficient  $H_2SO_4$  to neutralise  $100g$  of alkalinity expressed as calcium carbonate ( $CaCO_3$ ) equivalent.

If all the  $\varnothing_{sw}$  is oxidised the annual corrosion rate for the concrete can be predicted from:

$$C_{avg} = (11.5k/A) \varnothing_{sw} \quad (3)$$

$C_{avg}$  - average corrosion rate,  $mm/year$

$K$  - efficiency coefficient for acid reaction based on the estimated fraction of acid remaining on sewer wall. May be as low as  $0,3$  and will approach  $1,0$  for a complete acid reaction.

$A$  - Alkalinity of the cement-bonded material expressed as its calcium carbonate ( $CaCO_3$ ) equivalent; it varies from  $\pm 0,16$  for siliceous aggregate concrete to  $\pm 0,9$  for calcareous aggregate concrete;  $0,4$  for mortar linings.

$11,5$  - converts  $\varnothing_{sw}$  in  $g/m^2/h$ , into  $C_{avg}$ , in  $mm/year$

When combined with the equation for the flux of  $H_2S$  to the wall of a pipe the LFM equation is expressed as:

$$Az = 11.5 k \varnothing_{sw} L \quad (4)$$

$Az$  - additional concrete cover, required over reinforcement, (mm) (sacrificial layer)

$L$  - required design life of sewer in years

There are three options for preventing or minimising the corrosion in concrete sewers:

- preventing acid formation
- modifying concrete
- protecting concrete.

Acid formation can be prevented or minimized by adjusting the hydraulic design of the sewer. However, due to physical constraints this is not always possible and some corrosion can be anticipated. For most sewers modifying the concrete by changing the concrete components and/or providing additional cover to reinforcement is the most cost effective option. Protecting concrete by using an inert lining or coating is effective, but only economically justified when severe corrosion is predicted.

### 9.3 DEVELOPMENTS IN SOUTH AFRICA

Since the 1960's most concrete sewers in South Africa have been made using calcareous aggregates, usually dolomitic and the principle of a sacrificial layer. This solution followed the recommendations of a 1959 CSIR publication. The experience in Johannesburg where the first calcareous pipes were laid in 1960 and other cities and towns in South Africa indicates that this results in a considerable increase in a sewer's life. As far as can be established, there have been no reports of serious problems on sewers made using this approach.

However, concern had been expressed by local authorities and consultants that the "dolomitic aggregate" solution might not be adequate for certain sewers in the long-term. This concern was substantiated by application of the Life Factor Model (LFM), developed in the USA by Pomeroy and Parkhurst that quantifies the biogenic corrosion of concrete, to several sewers where severe corrosion was anticipated.

When the CSIR undertook a literature search during the 1980s, no reference could be found to field trials established to calibrate the actual performance of various sewer materials. Following several meetings of interested parties, a steering committee was formed and a decision taken to include an experimental section, with a bypass, as part of a sewer being installed at Virginia in the Free State. The LFM indicated that the conditions anticipated in this sewer

were so corrosive that the traditional solution would be unsuitable and a cementitious pipe would require an inert lining or coating.

There have been three phases to monitoring material performance and conditions in this sewer.

- Phase One was undertaken by the CSIR to monitor the conditions in the sewer and the performance of traditional sewer pipe materials in the sewer and subject to pure acid attack in a laboratory.
- Phase Two was undertaken by the University of Cape Town (UCT) to continue monitoring the conditions in the sewer and to investigate ways of simulating these conditions in a laboratory.
- Phase Three is being undertaken jointly by UCT and an independent consultant as a continuation of the second phase and involves measuring the actual corrosion that occurred during the first two phases; supervising the rehabilitation of the experimental section; and measuring the actual corrosion on various new materials to be calibrated for use in the LFM.

At the time of writing the experimental section of sewer has been rehabilitated and the actual corrosion on the samples installed during phase one has been determined and is summarised in Table 23 below. From this table it can be seen that measured average corrosion rates after 14 years for all the materials was somewhat greater than the estimates made following earlier inspections. As these measurements were taken on the samples removed from the sewer and the actual wall thicknesses could be measured, giving greater accuracy.

To date the LFM has been applied to PC concretes only.

The corrosion rates measured in this experimental section of sewer mean that the LFM can now be applied where other concretes are used. The effective alkalinity of alternative concretes can now be allocated values in excess of unity. In particular the effective alkalinity of an inert material can be taken as infinity. The LFM can now be used to calculate the required sacrificial layer thickness by incorporating a material factor,  $M_F$  that is the ratio of corrosion rate for the alternative material being considered and a standard concrete made from PC and siliceous aggregate.

By applying the LFM as described in equation 4 above to a particular sewer and assuming an 'A' value of 0.16 as would be appropriate for a standard siliceous aggregate concrete the required sacrificial layer can be established. The sacrificial layer thickness for another material can be calculated by multiplying this value by the appropriate material factor,  $M_F$  from Table 25.

$$Z_{\text{ANOTHER}} = 72 M_F k\phi_{\text{sw}} L \quad (5)$$

$M_F$  - Material Factor for chosen material and is obtained from Table 23.

This extension to the LFM has been called the Material Factor Model (MFM). The application of this and how it can be used to determine the most cost effective pipe material for a given sewer is described in section 9.5 that follows.

Based on the 5 year findings from the Virginia Sewer the concept of making a host pipe of one type of concrete to provide the strength and an additional layer of another concrete to cope with the corrosion was investigated. A effective technique for doing this was developed and since 1997 has been used on many of the major outfall sewers in South Africa.


**TABLE 23: MEASURED & ESTIMATED CORROSION AND MATERIAL FACTORS**

Material (cement/ Aggregate)	5 year estimate		12 year estimate		14 year measured		Material factor ***
	Total	Ave	Total	Ave	Total	Ave	
PC/SIL	>30	>6,0	>64	>6,0	> 105	> 7.5	1.000
PC/DOL	10 – 15	2 – 3	20 – 30	1,7 – 2,5	43	3.1	0.400
CAC/SIL	5 – 10	1 – 2	10 – 15	0,8 – 1,2	26	1.9	0.250
FC	10 - 12	2 +	20 - 25	1,7 – 2,1			0.320
CAC/DOL *	3,0	0,6	7,2	0,6	8,4	0,6	0.085
CAC/ALAG™ **							0.025

\* Values estimated on basis of other materials and performance of samples in sewer.

\*\*Much less than CAC/DOL-no mass loss 17 months in sewer and pH on surface >6,4

\*\*\*Average of maximum loss at side divided by corresponding value for PC/SIL.



The most commonly used combination of materials has been a host pipe made of PC/SIL concrete and a sacrificial layer of CAC/DOL. When such pipes are made an allowance of 3 to 5 mm is made for the interface between the two concretes.


#### 9.4. DESIGN AND DETAIL CONSIDERATIONS

There are many publications on sewer corrosion. However few have been written in a South African context and to date as far as can be established none have quantified the corrosion rates of non-PC concretes as described above. These do however address the issues of the hydraulic design and detailing of sewers. The following points should be considered when designing and detailing a sewer:

- The longer the sewage stays in the sewer the greater are the chances that it will turn septic and the rate of sulphide generation increase. Where practical retention times should be kept to a minimum.
- Slow flows inhibit the absorption of oxygen into fresh sewage causing an increase in sulphide generation. In addition slow flows could result in thicker slimes layers and silt build-up that in turn increase  $H_2S$  generation. Flow velocities at minimum discharge should be at least 0.7m/s
- Moisture condensation on sewer or manhole surfaces provides the habitat for the bacteria that produce  $H_2SO_4$ . Taking steps to reduce moisture condensation are not always possible.
- Junctions between sewers with different velocities can obstruct in the sewers with the slower flows causing long retention times in them. When sewers are joined the upstream gradients should be adjusted so that the entry velocities are as close as possible to each other.
- Most junctions are affected at manholes. Energy losses and turbulence are associated with the release of  $H_2S$  and the possibility of local corrosion. The inverts of such manholes should be carefully benched with smooth transitions to minimise energy losses and turbulence.
- If a fast flowing lateral discharges into a manhole benching as shown in Figure 33(a) and at the same invert level as that of the collector, the flow in the collector can be obstructed causing long retention times upstream of the junction. The fast flows should enter above, and in the

direction of the collector sewer, not at the same level and at as small an angle as possible, as shown in Figure 33(b).

Figure 33: Connection between collector and lateral.



The rate of  $H_2S$  generation in rising mains and siphons is much greater than in sewers flowing partly full because the slimes layer extends around the full pipe circumference, none of the gas generated escapes and there is no oxygen enrichment of the sewage. Severe corrosion can occur in sewers downstream of these especially when sewage retention times exceed much more than an hour. When the sewage discharges into the gravity section of sewer the accumulated  $H_2S$  is liberated and can cause severe local corrosion. Procedures for minimising retention times and the resultant corrosion are:

- Use the smallest practical pipe diameter for the full flowing section of sewer
- Make the section as short as possible
- Operate pumps frequently, particularly in early years of the system where low flows could result in the sewage upstream of the full flowing section becoming septic.

Sewage with a high BOD usually results in higher sulphide content and this could result in the corrosion of the structures at the purification works. Various measures that can be taken to reduce this are:

- If the BOD is very high, greater than 1 000 mg/l, pre-treat the sewage
- Lay the feed line to the dosing tank below the hydraulic gradient to exclude oxygen.

*In special cases the addition of hydrated lime to increase the sewage pH, or alternatively ventilating the outfall using a forced draught should be considered.*

*Careful hydraulic design and attention to detail has a positive contribution in reducing sewer corrosion. However they cannot eliminate the problems that could arise if the corrosion potential is severe and has not been identified by doing the necessary corrosion analysis. The above considerations should be used in combination with an application of the LFM and MFM when designing and detailing sewers; not as a substitute an analysis.*

## **9.5 PIPE MATERIAL CHOICE FOR SEWERS**

*There are several concrete pipe alternatives that could be used for sewers. These are:*

- *Host pipe and sacrificial layer made from PC/SIL*
- *Host pipe and sacrificial layer made from PC/DOL*
- *Host pipe made from PC/DOL or PC/SIL and sacrificial layer made from CAC/SIL*
- *Host pipe made from PC/DOL or PC/SIL and sacrificial layer made from CAC/DOL*
- *Host pipe made from PC/DOL or PC/SIL and an HDPE lining cast in.*

*The relative corrosion rates of these sacrificial layer materials are given in the Table 23. By applying the LFM and the MFM as described above a technically sound solution that is also the most cost effective alternative for a sewer operating under a particular set of circumstances can be selected.*

*As the primary function of a sewer is to convey wastewater the first item that should be addressed is the pipe size required. Ideally this should be based on two limiting values of velocity namely:*

- *A minimum value (0,7m/s) at low flow that will ensure self-cleansing.*
- *A maximum value of 0,8 times the critical velocity to prevent excessive turbulence.*

*The internal diameter (ID) and the hydraulic properties obtained from these calculations should be used in combination with the effluent properties to predict the potential corrosion for the required design life assuming a PC/SIL concrete. The relative corrosion rates of other types of concrete being considered for the project should then be calculated based on the details given in Table 23. The sacrificial layer thickness with an appropriate allowance for an interface if the sacrificial layer and host pipe are made from different concretes should be added to*

*the required internal diameter to give the host pipe internal diameter.*

*From the installation conditions do a preliminary assessment of the pipe class that will be required based on the worst-case scenario as given in Table 23. If the pipe class indicated were 75D or 100D then the outside diameter (OD) of the pipe would be 1.2 times the indicated host pipe ID. If the pipe class indicated was 50D or less then the outside diameter would be 1.14 times the host pipe ID.*

*The manufacturers brochures should be consulted to determine the nearest actual external diameter that would give at least the external diameter as indicated by the calculations done following the above procedure. This should be done for each of the solutions being evaluated as when severe corrosion is predicted there will be a significant difference between the minimum required host pipe OD's and this could mean that the pipes using a different corrosion control measures would be made in moulds of different OD's. This is illustrated in the example that follows.*

*Once the mould OD's for the different solutions have been established the exercise should be repeated for each of these alternatives but in the reverse order namely:*


- *For the required OD determine the pipe strength and class required to handle the installed conditions.*
- *Add the required sacrificial layer or lining thickness to the host pipe ID to determine the actual pipe ID.*
- *Check the hydraulics of the sewer using the actual ID.*

*The designer is now in a position to get budget prices from the suppliers so the alternatives can be compared on an economic basis.*

*Example: determine the most cost effective pipe with an actual ID of 900mm for a range of Az values, namely 5, 10, 20 and 40. Assume that the required pipe class is 100D.*

*As the corrosion potential increases the solutions that are more costly to produce actually become more cost effective solutions. The following shows this:*

- *If there is any corrosion potential at all the PC/SIL solution will be the most costly and the PC/DOL solution where the host pipe and sacrificial layer is made from the same material is the most cost effective.*



- Where corrosion potential becomes greater ( $15 < Az < 30$ ) the CAC/DOL sacrificial layer and a host pipe of a standard concrete will be the most cost effective.
- Where corrosion potential becomes severe ( $Az > 30$ ) the HDPE lining cast into the host pipewill be the most cost effective

It should be noted that the costs used in this exercise are hypothetical and that do make this comparison on an actual project it would be necessary to obtain actual prices from the pipe suppliers.

Although a lining of CAC/SIL would be technically sound it would not be cost effective unless it was very expensive to transport dolomitic aggregate to the manufacturing plant.

From the above example it can be seen that all sewer pipes and manholes should be manufactured using calcareous aggregates even if no corrosion is expected. The concrete made for these should

contain not more than 25% insolubles when tested in hydrochloric acid. (Details of the test method are given in SANS 676.) In some parts of South Africa aggregates are available with insolubility levels of 12% to 18%. If available the lowest practical level should be specified.

The standard sacrificial layer thicknesses used in South Africa are 13 mm for pipes up to 1050 mm in diameter and 19 mm for diameters larger than this. If the corrosion analysis indicates that these thicknesses are inadequate and a more costly material cannot be justified then a thicker sacrificial layer should be specified. To ensure that the hydraulic requirements will be met the minimum internal diameter and the sacrificial layer thickness should be specified. When the sacrificial layer and host pipe are made from different concretes an allowance should be made for the interface between the two concretes. Under these circumstances it would be realistic to consider the design values for the standard sacrificial layers as being minimum values of 10 and 15 mm instead of nominal values of 13 and 19 mm.

MATERIAL	PC/SIL			PC/DOL			CAC/DOL		
	5	10	20	5	10	20	5	10	20
Az VALUE	5	10	20	5	10	20	5	10	20
PIPE ID-	900	900	900	900	900	900	900	900	900
SACR L	30	60	125	12	24	50	5	9	15
HOST ID	960	1020	1150	924	948	1000	910	918	918
PIPE OD	1152	1224	1380	1108.8	1137.6	1200	1092	1102	1116
HOST - kg	822	928	1179	757	803	892	738	753	771
SACR L - kg	226	467	1038	89	178	385	37	66	111
TOTAL - kg	1046	1395	2217	845	981	1277	775	819	882
% HOST PRICE	145	193	307	117	136	177	123	132	153

	PC/DOL				CAC/DOL				HDPE
	5	10	20	40	5	10	20	40	all
Az VALUE	5	10	20	40	5	10	20	40	all
PIPE ID-	900	900	900	900	900	900	900	900	900
SACR L	12	24	50	100	5	9	15	25	0
HOST ID	1100	910	1000	1100	930	950	950	950	905
PIPE OD	1320	1116	1200	1320	1140	1102	1116	1140	905
HOST - kg	757	803	892	1079	738	753	771	805	787
SACR L - kg	89	178	385	811	37	66	111	187	0
TOTAL - kg	845	981	1277	1889	775	819	882	992	0
% HOST PRICE	117	136	177	262	123	132	153	189	178

This table clearly illustrates the impact of the corrosion potential on the cost effectiveness of the various materials commonly used as corrosion control measures for sewers in South Africa.

## 9.6. SACRIFICIAL THICKNESS AND ALLOWABLE CRACK WIDTHS

Where an increased sacrificial layer thickness is specified the allowable crack width should be increased in proportion to the increase in concrete cover to steel. The allowable crack width can be calculated from the formula (6) that is given in SANS 677.

$$r = q(t-x) / [t-x-C_2] \quad (6)$$


- $r$  — allowable crack width for a sacrificial layer thickness of  $C_2$  in mm  
 $q$  — allowable crack width for a pipe with standard cover to steel in mm  
 $t$  — total wall thickness of pipe in mm  
 $x$  — distance from the outside surface of pipe to the neutral axis in mm

$$C_2 = C - C_1 \quad (7)$$

- $C$  — total concrete cover to inner steel reinforcement cage in mm  
 $C_1$  — standard specified concrete cover to inner steel reinforcement cage in mm

The neutral axis of the pipe can be taken as being half the host pipe wall thickness. The relationship between these symbols is shown in Figure 34 below.

Figure 34: Relationship between crack width and sacrificial layer



Example: If a 900 mm diameter concrete pipe with a standard wall thickness of 93 mm has a sacrificial layer of 20 mm, what is the allowable crack width at proof load? Standard cover to steel is 10 mm.

Neutral axis,  $x = 93/2 = 46.5$  mm

$C = C_1 + C_2 = 10 + 20 = 30$  mm and  $r = 0.25[113 - 46.5]/[113 - 46.5 - 20] = 0.36$  mm

There are two practical factors that should be considered when sacrificial layers that are thicker than standard ones are specified, namely:

- If the sacrificial layer is thicker than one third of the wall thickness the reinforcement will be close to the centre of the pipe wall and will not be effective in controlling cracks.

- If the sacrificial layer thickness is more than twice the standard concrete cover to reinforcement the crack widths that could be accepted if equation (6) were blindly applied could be excessive and allow aggressive elements to enter the cracks and move the corrosion front closer to the reinforcement.

The ACPA Concrete Pipe Handbook states that problems have not been experienced with pipes that have cracks in them of up to 0.5 mm when the concrete cover to reinforcement is 25 mm. As this cannot be substantiated by any scientific study it is recommended that the serviceability limit for crack widths be limited 0.4 mm even if equation (6) above indicates a larger value.


By applying the correct procedure for predicting corrosion and then choosing the pipe material that cost effectively meets the requirements the above problems will in general be avoided.

## 10. PORTAL CULVERT STRENGTHS

### 10.1 GENERAL


The terms used with portal culvert installation are detailed in Figure 35 below.

Figure 35: Terminology for portal culverts



As portal culverts are rectangular two dimensions determine their size. Hence, the relationship between the load to be carried and the required strength cannot be simplified as it can with pipes. Hence, the strength required is determined by using a direct approach. The procedure adopted is:

- Determine the structural properties of the portal



- Calculate loads and load combinations
- Calculate the bending moments and shear forces generated in the portal by the various load combinations
- Determine the bending moment and shear force envelopes that cover all the loading cases
- Determine combinations of test loads to model the installed bending moment and shear force envelopes.

This procedure can be followed by using ultimate values for both the installed and test loading conditions or by factoring the installed parameters and determining the proof load parameters that match them.

## 10.2. DETERMINING PORTAL CULVERT STRENGTHS

As mentioned at the beginning of this handbook, there is no National Standard for determining the loads on or Strengths of Portal Culverts. In TMH7, the Code of Practice for the Design of Highway Bridges and Culverts in South Africa, Clause 2.3.3.1, provision has been made for three solution levels, namely:

*“General: With due recognition of the complexity of the problem of determining loading on culverts, but also of the need for simple procedures which can be used routinely, provision is made for the three-fold approach, viz:*

- The application of simple design rules that can be applied to rigid and flexible culverts but that require the use of increased partial safety factors which allow for the approximate nature of the formulae used.
- The application of more sophisticated design theories to rigid and flexible culverts that take into account the type of culvert, the properties of the undisturbed ground and the fill materials as well as the effects of the actual width of excavation, and the positive or negative projection. These theories also allow for the use of reduced partial safety factors. (In positive and negative projecting culverts, the tops of the structures are above and below undisturbed ground level respectively.)
- The application of sophisticated design theories or the design techniques based on the phenomenological approach to flexible and special types of culvert that required more accurate assessments of soil-structure interaction.

*This Code covers the first approach only, which is an extension of the AASHTO and CPA formulae. The designer shall use his discretion in deciding on the best applicable method for any particular case and is referred to publications on the subject.”*

*In the simplified approach the earth loading has been reduced to four combinations of foundation and installation conditions, namely:*

*Condition 1: Culverts in trench on unyielding foundation with no projection.*

*Condition 2: Culverts untrenched on yielding foundation.*

*Condition 3: Culverts untrenched on unyielding foundation for  $H > 1.7B$*

*Condition 4: Culverts untrenched on unyielding foundation for  $H < 1.7B$*

*Where H - fill height in metres*

*B - if trenched overall trench width, or if untrenched overall culvert width, in metres.*

*Conditions 1 and 2 correspond to the geostatic loading condition and 3 and 4 to the positive projection installation condition with an  $P_r$  ratio of 1.*

*Approximate methods for determining the effects of traffic loading on rigid conduits are given in Clause 2.6.6 of TMH7.*

*This combination of the earth and traffic loading was applied to the standard portal culvert dimensions to determine the product strengths required. These strengths were compared with those of the standard S-load culverts and the appropriate classes selected.*


*The relationship between standard portal culvert classes and maximum fill heights for TMH7 loading conditions applied to the standard sizes is given in Table 24.*

*The assumptions, and clauses from TMH7 Parts 1 and 2 used to compile this table are:*

- The table is applicable to rectangular portal culverts only
- When sizes other than given in this table the manufacturer should be contacted.
- A minimum fill height of 300 mm over the culvert units. Where this cannot be achieved a 100 mm reinforced concrete slab must be used.

**TABLE 24: MAXIMUM FILLS: S-LOAD PORTAL CULVERTS UNDER TMH7 LOADING.**

Culvert span x height in mm			Installation conditions 1&2		Installation conditions 3&4	
600	X	300	200 S	10.2	200 S	5.6
600	X	450		11.0		6.0
600	X	600		12.0		6.4
750	X	300	175 S	8.7	175 S	4.9
750	X	450		9.2		5.2
750	X	600		10.0		5.5
750	X	750		10.5		5.8
900	X	300	175 S	8.6	175 S	4.8
900	X	450		9.0		5.1
900	X	600		9.5		5.3
900	X	750		10.0		5.6
900	X	900		10.2		5.8
1200	X	300	150 S	7.1	150 S	4.1
1200	X	450		7.4		4.3
1200	X	600		7.7		4.4
1200	X	900		8.2		4.7
1200	X	1200		8.8		5.0
1500	X	450	100 S	4.7	100 S	3.0
1500	X	600		4.9		3.1
1500	X	900		5.3		3.3
1500	X	1200		5.6		3.5
1500	X	1500		6.0		3.7
1800	X	600	75 S	3.3	75 S	2.4
1800	X	900		3.6		2.5
1800	X	1200		3.8		2.7
1800	X	1500		4.0		2.8
1800	X	1800		4.3		2.9
2100	X	600	75 S	3.3	75 S	2.4
2100	X	900		3.5		2.6
2100	X	1200		3.7		2.7
2100	X	1500		3.9		2.8
2100	X	1800		4.1		2.9
2100	X	2100	4.3	3.0		
2400	X	600	75 S	3.2	75 S	2.4
2400	X	900		3.4		2.5
2400	X	1200		3.5		3.5
2400	X	1500		3.7		3.7
2400	X	1800		3.8		3.8
2400	X	2400		4.0		4.1
3000	X	900	75 S	3.2	75 S	2.5
3000	X	1200		3.3		2.6
3000	X	1500		3.4		2.7
3000	X	1800		3.5		2.7
3000	X	2400		3.7		2.9
3000	X	3000		3.1		2.7
3600	X	900	75 S	3.1	75 S	2.5
3600	X	1200		3.2		2.6
3600	X	1500		3.3		2.6
3600	X	1800		3.3		2.7
3600	X	2400		3.5		2.8
3600	X	3000		3.5		2.7



- Standard traffic loading (SN A, B and C) as described in Clause 2.6.1.2
- Fill material unit weight 20 kN/m<sup>3</sup> [Clause 2.3.1]
- Concrete unit weight 24 kN/m<sup>3</sup> [Clause 2.2.1]
- Horizontal earth pressure 7,8 kN/m<sup>2</sup> per metre depth [Clause 2.4.2]
- Ultimate Limit State load factors Table 7.

If portal culverts are required where the fill over them is less than 300 mm or more than the amount stated in this table the loads must be calculated using the procedures in TMH7 and the strength by following the procedure given at the end of section 10.1 above.

### 10.3 PORTAL BASE SLABS

Most pre-cast portal culverts are placed on cast in place base slabs. These should be designed to take the actual loads that will be applied to them.

It is important to realise that the moments and shears generated by the installed loads on base slabs are different from those generated on the portal unit. The total load on the portal unit will be transferred down the legs to the base slab. The moments and shears will then be transferred through the base slab to the founding material. If this material is unyielding the load will be transferred directly through the slab generating shear but no bending moments. If however, the material under the slab is yielding, both shear forces and bending moments will be generated.

The installed loads on the portal crown are assumed to be distributed over the whole width of the portal, except for the very low fill heights where there are concentrated loads from the traffic. The test loads on the portal crown are concentrated live loads. If there were no factoring of installed loads, the test loads would be about half the installed ones. Hence, the test loads model the installed loads on the portal crown, but do not model the installed loads on the base slab.

If pre-cast bases are to be used under crown units, a check should be done to ensure that they are sufficiently strong to take the imposed loads.

and hydrostatically tested at the factory before delivery to site to ensure that they will meet the structural requirements specified. As the pipes are jointed on site they need to be tested on site to ensure that the pipeline will meet its operating requirements. Apart from a visual inspection the only field-testing needed on a concrete pipeline is one for leakage. This gives the assurance that the installed pipeline will meet the water tightness requirements.

The water test is carried out as follows:

- Close the section of pipeline to be tested with bulkheads or plugs. As these will be subject to considerable forces they should be designed and installed to ensure that they can withstand these with an adequate safety factor.
- Open the air valves and slowly fill the test section with water to ensure that all the air escapes.
- Keep the test section under a slight pressure for 3 to 5 days to allow the pipes to absorb water
- If pipes were exposed for more than a month additional time may be needed for this.
- During this period check the sealed ends and joints for leaks and the rate at which water has to be added to maintain the pressure.
- When the rate of adding water stabilises increase the pressure to the required value.

SANS 1200-LD prescribes that sewers should be tested with a water head of not less than 1.2 m and not more than 6.0m. The loss allowance prescribed is not more than 6 litres/100mm of diameter/100m/hour.

Pressure pipelines are tested in the same way but the requirements are more stringent. A testing schedule that gives the pressure for each section should be compiled to ensure that the lower class pressure pipes are not overstressed.

The full-scale water testing of large diameter sewers and pipelines is a difficult and costly exercise. When available, special joint testing equipment that applies water pressure to one joint at a time is used. This equipment has to be used with care and it should be appreciated that it is not testing the joint that has already been factory tested, but the jointing that has been done on site. Hence the pressures used are not the same as those for which the pipeline is rated. In most cases when a sewer is man entry ( $\geq 900$  mm in diameter) and below the water table as frequently occurs with this size, it can be physically inspected to check for leaks.

## 11. FIELD TESTING

### 11.1 WATER TEST

Pipelines consist of pipes and joints. Concrete pipes used for sewers and low-pressure pipelines are load

Concrete has the property of autogenous healing and hair cracks or damp spots should not be cause for rejection, as this type of leakage will be stop within days of the pipe surface being exposed to a moist environment.

## 11.2 AIR TESTING

The water testing of sewers is seldom practical especially in a country such as South Africa where water is scarce and may not be available for the testing of sewers. Air testing of concrete sewers is an effective way for identifying isolated sections that are leaking as poor joints or damaged pipes. As air and water have different properties this test is not an indicator of the water tightness of the pipe wall. This testing can therefore be used as an acceptance test but not as justification for rejection. If there is a dispute the final acceptance or rejection of a sewer should be based on a water test.

This test is conducted in a similar way to the water test. However as the intention of this is to find isolated problems the air pressure inside the section being tested is only just above atmospheric. The procedure followed is:

- Seal the ends of the section to be tested with bulkheads or plugs; making sure that the safety factor of blow out to test pressure is at least 2.
- One of the bulkheads is fitted with connections to an air source, a pressure release valve and a pressure gauge or monometer.
- Air is added to the test section to increase the internal pressure to a prescribed amount above atmospheric. This must allow sufficient time for this to stabilise, as there may be differences between the air and pipe wall temperatures.
- Once the air pressure within the test section has stabilised the air supply is stopped and the time in seconds that it takes for a given pressure drop is measured. The rate of air loss is then calculated.

The sewer is then inspected to determine whether there are any joints or damaged sections that are leaking. These leaks can usually be identified by the sound of escaping air. If no localised leaks are identified and the rate of pressure drop is unacceptable the exposed sewer is sprayed with soapy water to help find any problem areas. Leaking joints or damaged sections of pipe must be repaired using means that are approved by the project engineer.

Section 7 of SANS 1200-LD prescribes the pressures and procedures that should be used for the air testing of sewers namely:

- An initial pressure of 3.75kPa(375mm of water)
- Once the pressure stabilises, reduce it to 2.5kPa(250mm of water)
- Switch off the machine and measure how long it takes for the pressure to drop to 1.25kPa(125mm of water)
- The minimum acceptable time for this drop to take place is 2 minutes/100mm diameter

Whenever possible defects should be repaired with the pipes in place. Only when pipes have been incorrectly installed or there has been damage due to soil movements should the replacement of pipes be considered. If this is necessary it must be done from manhole to manhole so that the whole installation is redone and the possibility of relative settlement between sections of sewer is eliminated.


Should this spraying of soapy water on the exposed pipe show sections of pipe where bubbles form this will probably be due the pipes having dried out as a result of being exposed for prolonged period (in excess of 6 weeks). When these pipes are exposed to the moist sewer atmosphere the concrete will take up moisture and the microstructure will seal.

## 11.3 SOIL DENSITY TEST

This needs to be checked:

Where specifications call for minimum densities of backfill or bedding material, these are normally given as a percentage of the Modified Proctor Density. The test is carried out in the following way:


- Samples of the various materials to used are obtained
- Each sample is dried and then prepared at various moisture contents.
- For each of the moisture contents five layers are compacted in a 0.95 litre mould.
- Each layer receives 25 blows from a 4.54 kg hammer falling from 457 mm
- The optimum moisture content is the moisture content corresponding to maximum dry density. This maximum soil density is referred to as the Modified Proctor Density.



Density tests are done on the compacted backfill or bedding material on the site and then compared to the


Modified Proctor Density to check that these materials have been placed to the required densities.

Figure 36: Moisture content and density relationship



## BIBLIOGRAPHY

1. American Concrete Pipe Association: *Concrete Pipe Handbook*, Virginia USA, 1981.
2. Clarke N W B. *Buried Pipelines: a manual of structural design and installation*. London, Maclaren, 1968
3. Portland Cement Association: *Handbook of Concrete Culvert Pipe Hydraulics*. Skokie, 1964
4. SANS 10102-2: *Selection of pipes for buried pipelines Part 2: Rigid pipes*
5. SANS 1294: *Precast Concrete Manhole sections and slabs*
6. SANS 676: *Reinforced Concrete Pressure Pipes*
7. SANS 677: *Concrete non-pressure pipes*
8. SANS 986: *Precast reinforced concrete culverts*
9. SANS 10102: *The selection of pipes for buried pipelines. Part 1: General Provisions*
10. SANS 10102: *The selection of pipes for buried pipelines. Part 2: Rigid Pipes*
11. SANS 1200 DB: *Earthworks (Pipe Trenches)*
12. SANS 1200 L: *Medium-pressure Pipelines*
13. SANS 1200 LB: *Bedding (Pipes)*
14. SANS 1200 LE: *Stormwater Drainage*
15. SANS 1200 LD: *Sewers*
16. SANS 1200 LG: *Pipe Jacking*
17. Hart-Davis, Adam. *What the Victorians did for us*. Headline Book Publishing, London, 2001, pp.59—61.
18. *Ibid*, p142.
19. Council for Scientific and Industrial Research (CSIR), Division of Building Technology. *Corrosion of concrete sewers*. CSIR, Pretoria. Series DR12. 1959.
20. Bealey, Mike, Duffy, John J, Preuit, Russell B, Stuckey, Robert E. *Concrete pipe handbook*. American Concrete Pipe Association, Virginia, USA, 1981, pp. 7-22 — 7-34.
21. Council for Scientific and Industrial Research (CSIR), Division of Building Technology. *Report on phase 1 of sewer corrosion research: The Virginia sewer experiment and related research*. CSIR, Division of Building Technology, Pretoria, 1996, p.40.
22. Goyns, A. *Virginia sewer rehabilitation. Progress report no 1. A project being undertaken by the Pipe and Infrastructural Products Division of the CMA. PIPES CC Centurion, 2003, pp.12 — 14.*
23. Goyns, A. *Virginia sewer rehabilitation. Progress report no 2. A project being undertaken by the Pipe and Infrastructural Products Division of the CMA. PIPES CC Centurion, 2004.*
24. Kienow, KK, Pomeroy, RD. *Corrosion resistant design of sanitary sewer pipe*. ASCE Convention and exposition, Chicago, USA, 1978.
25. McLaren, Frederick R. *Design manual: sulfide and corrosion prediction and control*. American Concrete Pipe Association, Virginia, USA, 1984. 26. *Ibid*, p.4-4.
27. Bowker, Robert PG, Smith, John M, Webster, Neil A. *Design manual: Odor and corrosion control in sanitary sewerage systems and treatment plants*. Centre for Environmental Research Information, US Environmental Protection Agency, Cincinnati, 1985, p.23.
28. McLaren, Frederick R. *Design manual: sulfide and corrosion prediction and control*. American Concrete Pipe Association, Virginia, USA, 1984, p.4-4.
29. Council for Scientific and Industrial Research (CSIR), Division of Building Technology. *Report on phase 1 of sewer corrosion research: The Virginia sewer experiment and related research*. CSIR, Division of Building Technology, Pretoria, 1996.
30. Goyns, A. *Virginia sewer rehabilitation. Progress report no 1. A project being undertaken by the Pipe and Infrastructural Products Division of the CMA. PIPES CC Centurion, 2003, pp.9—14.*
31. Council for Scientific and Industrial Research (CSIR), Division of Building Technology. *Report on phase 1 of sewer corrosion research: The*



*Virginia sewer experiment and related research. CSIR, Division of Building Technology, Pretoria, 1996, p.6.*

32. *Ibid, p.46, p.102.*

33. *Fourie, CW. Biologically induced sulphuric acid attack on concrete samples in the experimental sewer section at Virginia. Department of Civil Engineering, University of Cape Town, 2002.*

34. *Dumas, TH. Private communication, Lyon, France, June 1994.*

35. *resistance to sulphur-oxidising bacteria. Materials Performance, Vol26, No3, March 1987, pp. 14-17.*

36. *Goyns, A. Virginia sewer rehabilitation. Progress report No 1. A project being undertaken by the Pipe and Infrastructural Products Division of the CMA. PIPES CC Centurion, 2003, pp.7—14.*

37. *Fourie, C.W. Biologically induced sulphuric acid attack on concrete samples in the experimental sewer section at Virginia. Department of Civil Engineering, University of Cape Town, 2002, p.1.*

38. *Council for Scientific and Industrial Research (CSIR), Division of Building Technology. Report on phase 1 of sewer corrosion research: The Virginia sewer experiment and related research. CSIR, Division of Building Technology, Pretoria, 1996, p.93.*

39. *Fourie, CW. Biologically induced sulphuric acid attack on concrete samples in the experimental sewer section at Virginia. Department of Civil Engineering, University of Cape Town, 2002, p.9.*

40. *Ibid, p.2, p.6.*

41. *Ibid, p.11.*

42. *Ibid, p.8.*

43. *McLaren, Frederick R. Design manual: sulfide and corrosion prediction and control. American Concrete Pipe Association, Virginia, USA, 1984, pp.5-2—5-4.*

44. *Bowker, Robert PG, Smith, John M, Webster, Neil A. Design manual: Odor and corrosion control in sanitary sewerage systems and treatment plants. Centre for Environmental*

*Research Information, US Environmental Protection Agency, Cincinnati, 1985, p.25.*

45. *Ibid, p.25.*

46. *Council for Scientific and Industrial Research (CSIR), Division of Building Technology. Report on phase 1 of sewer corrosion research: The Virginia sewer experiment and related research. CSIR, Division of Building Technology, Pretoria, 1996, p.58.*



## PIPES & INFRASTRUCTURAL PRODUCTS PRODUCER MEMBERS (JULY 2009):

Concrete Units	(021) 386-1923
Infrasat	(011) 876-5500
Rocla	(011) 670-7600
Salberg Concrete Products	(011) 357-7600
Southern Pipeline Contractors	(011) 914-8500



**CU** CONCRETE UNITS

**INFRASET**  
THE AVENIS GROUP

**ROCLA**

**Salberg  
Concrete  
Products**  
(Pty) Ltd

**SOUTHERN PIPELINE  
CONTRACTORS**

**SABS** MARK  
HOLDERS

**CONCRETE  
MANUFACTURERS  
ASSOCIATION**  
Quality cast in concrete

Block D, Lone Creek, Waterfall Office Park, Bekker Road Midrand.  
PO Box 168 Halfway House 1685  
Tel +27 11 805 6742, Fax +27 86 524 9216  
e-mail: main.cma@gmail.com website: www.cmapipes.co.za